Bleaching Earths as Powerful Additives for Ru-Catalyzed Self-Metathesis of Non-Refined Methyl Oleate at Pilot Scale

Jessica Allard, Idriss Curbet, Guillaume Chollet, Fabien Tripoteau, Sophie Sambou, Frédéric Caijo, Yann Raoul, Christophe Crevisy, Olivier Baslé, Marc Mauduit

► To cite this version:

Jessica Allard, Idriss Curbet, Guillaume Chollet, Fabien Tripoteau, Sophie Sambou, et al.. Bleaching Earths as Powerful Additives for Ru-Catalyzed Self-Metathesis of Non-Refined Methyl Oleate at Pilot Scale. *Chemistry - A European Journal*, 2017, 23 (52), pp.12729-12734. 10.1002/chem.201703049 . hal-01614771

HAL Id: hal-01614771

<https://hal-univ-rennes1.archives-ouvertes.fr/hal-01614771>

Submitted on 26 Oct 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Bleaching Earths as Powerful Additives for Ru-Catalyzed Self-Metathesis of Non-Refined Methyl Oleate at Pilot Scale.

Jessica Allard,^[a,b] Idriss Curbet,^[a] Guillaume Chollet,^[c] Fabien Tripoteau,^[d] Sophie Sambou,^[b] Frédéric Caijo,^[d] Yann Raoul,^[b] Christophe Crévisy,^[a] Olivier Baslé^[a] and Marc Mauduit^{[a] *}

Dedicated to

Abstract: A practical and cost-effective ruthenium-catalyzed self-metathesis of non-refined methyl oleate (85%) derived from Very High Oleic Sunflower Oils (VHOSO) was demonstrated at pilot scale using a robust and kg-scale commercially available SIPr-M71 pre-catalyst. The simple addition of 1 wt% bleaching earths (Tonsil 110FF) to a thermally pretreated oil could efficiently prevent catalyst deactivation. Remarkably, without the need for filtration, the catalytic system was able to achieve a turnover number of more than 744000 at a catalyst loading of only 1 ppm. At large scale (up to 200 Kg), the equilibrium of the self-metathesis reaction was reached within 1 hour at 50 °C under neat conditions at a very low 5 ppm catalyst loading to produce the expected primary metathesis products (PMP), i.e. the 9-octadecene and the dimethyl-9-octadecenoate with a productive TON of 94900.

Scheme 1. Ru-catalyzed Self-metathesis of unsaturated fatty ester methyl oleate (Z)-1 derived from vegetable oils.

Considering the ineluctable rarefaction of fossil resources, the catalytic transformation of biomass derivatives into valuable fine chemicals constitutes a promising alternative, which could be in high demands in the near future.^[1] Among the available renewable resources, natural oils have both the advantage of containing various reactive organic functions (e.g. alkenes, alcohols, acids, esters) and to be currently produced at multi-million tons/year.^[2] The self-olefin metathesis (SM)^[3] of unsaturated fatty acids/esters from vegetable oils represents one of the most eco-efficient transformations with a remarkable low carbon footprint.^[4] For instance, the Ru-catalyzed SM of methyl oleate (MO) (Z)-1, derived from various oils (e.g. soybean, canola or sunflower), produces two highly desirable molecules (9-octadecene (E/Z)-2 and dimethyl-9-octadecenoate (E/Z)-3) as primary metathesis products (Scheme 1).^[4] The former can be readily converted into bio-sourced lubricants, surfactants or plasticizers,^[5] while the latter is considered as a precursor of monomers for the production of bio-sourced materials.^[6] In the last two decades, significant breakthroughs have been accomplished in metathesis of oleochemicals either

by academics or industrial companies, thanks to the development of robust and kg-scale commercially available Ru-based catalysts (Figure 2). For instance, Ru-2b was able to catalyze the SM of 1 at loadings as low as 1 ppm affording PMP 2 and 3 in 45% conversion at the equilibrium (Eq. b, Scheme 1) with the highest turnover number (TON) of 440 000 reported so far.^[7] The thienylmethylidene catalyst Ru-4 demonstrated also an impressive reactivity towards MO reaching a TON of 250 000.^[8] Nevertheless, the economical viability of industrial processes at multi-ton scale depends not only on the catalyst efficiency and selectivity,^[9] but also on the quality of the involved raw materials.^[2b] In fact, such remarkable catalytic metathesis activities could not be reached without requiring prior alumina filtration of a costly high-purity grade of MO (>99%)^[10], that is incompatible with an industrial process.

Figure 1. Benchmark of kg-scale commercially available Ru-1-6 pre-catalysts commonly used in metathesis of oleochemicals.

- [a] Dr. J. Allard, I. Curbet, Dr. C. Crévisy, Dr. O. Baslé, Dr. M. Mauduit
Ecole Nationale Supérieure de Chimie de Rennes, UMR CNRS
6226, 11 Allée de Beaulieu, CS 50837, 35708 Rennes Cedex 7,
France
E-mail: marc.mauduit@ensc-rennes.fr
- [b] Dr. J. Allard, Dr. S. Sambou, Dr. Y. Raoul
OLEON SAS, Venette BP 20609, 60206 Compiègne Cedex, France
- [c] Dr. G. Chollet
ITERG, 11 rue Monge – Parc industrie Bersol 2, 33600 Pessac,
France
- [d] Dr. F. Tripoteau, Dr. F. Caijo
DEMETA SAS, 6 rue Pierre-Joseph Colin, 35000 Rennes, France

Supporting information for this article is given via a link at the end of the document.

Because the pre-treatment of the oleo-raw materials represents a key success factor for a cost-effective metathesis process, many efforts have been made to address this concern.^[11] Several methodologies to trap catalyst poisoning species present in vegetable oils (e.g. peroxides, phosphates, sulfates, soap...) were reported with varying degrees of success. The use of reductive reagents, inorganic bases or metallic alcoholates followed by successive aqueous washes and then filtration through a sorbent such as activated charcoal, alumina, magnesium silicate or celite proved to be efficient.^[12] The thermal pre-treatment (100 °C) of methyl fatty esters under vacuum in combination with small amounts of a mix of sorbents (magnesium silicate/celite) represents the most effective process to date, allowing after filtration, the metathesis reaction with less than 10 ppm of catalyst loadings (with Ru-1).^[12d] However, due to a noticeable loss of the raw material during the filtration (up to 20 wt.%), all these pretreatments would have significant impact on the total cost of production. Therefore, the development of a simple, ton-scalable, and cost-effective olefin metathesis process for the conversion of renewable fatty esters is still in high demands. *Herein, we report an efficient ruthenium-catalyzed self-metathesis process to convert non-refined MO 1 (85%) derived from Very High Oleic Sunflower Oils (VHOSO) into corresponding PMP 2 and 3 at pilot scale using a robust commercially available M71 complex Ru-6a^[13] in presence of bleaching earths as additives to prevent the catalyst deactivation.*

We initiated our study by evaluating in self-metathesis a refined oil containing 94%^[14] of methyl oleate (Z)-1, derived from two successive recrystallizations in acetone (at -37 and -60 °C, respectively) of the VHOSO raw material (scheme 2). Without any pre-treatment, up to 0.05 mol% (500 ppm) of Ru-6a was needed to convert 89% of (Z)-1 within 15 min at 50 °C under neat condition and to reach the equilibrium (Eq. b), affording 2 and 3 in 20 and 22 wt%, respectively.^[15] A significant amount of methyl elaidate (E)-1 was also formed (41 wt%, see ESI for details). It is also important to note that below a catalyst loading of 400 ppm, no reactivity was observed. This result clearly demonstrated that, despite the robustness and high stability of the M71 pre-catalyst,^[13] the presence of certain substrate impurities has a dramatic effect on catalyst efficiency. Therefore, with the objective to reach an optimal catalytic process, it appeared important to us to clearly identify these poisons and to adapt accordingly. A large variety of organic molecules can be found in vegetal oils (Figure 2).

Scheme 2. Self-metathesis of MO (Z)-1 derived from refined VHOSO (94% of purity) catalyzed by SIPr-M71 Ru-6a. [a] Conversion of (Z)-1, monitored by GC (see ESI for details). [b] Percentage per weight of the composition of the crude at the equilibrium, determined by GC (see ESI). [c] E/Z ratio = 4/1.

Some are naturally present (**Np1-3**), some are formed during the hydrolysis (**Hp1-2**) or during the esterification process (**Ep1-3**) to produce fatty acid/esters, and some are resulting from decomposition by oxidation and/or polymerization (**Dp1-3**). Because, each of them can act as a potential poison towards either the ruthenium pre-catalyst or the catalytic active species, we decided to investigate their influence onto the rate of the SM reaction (figure 3 and SI).

Figure 2. Benchmark of molecules frequently present in fatty esters (**Np**: natural products; **Hp**: hydrolysed products; **Ep**: products from esterification; **Dp**: decomposed product)

Figure 3. Kinetic profiles of the SM of MO (Z)-1 catalyzed by Ru-6a in presence of additives **Hp** (a) and **Dp** (b). [a] Conditions: Ru-6a (0.05 mol%), additive (10 wt%), 50 °C, neat. [b] Percentage per weight of 2/3 in the crude, determined by GC (see ESI).

While the voluntary contamination with 10 wt% of lecithine (**Np1**), α-tocopherol acetate (**Np2**), sterols **Np3** or **Ep1-3** (i.e. Glycerol, water and methanol) had no effect on the rate of the metathesis reaction (see ESI for details), a noticeable effect was observed after the addition of by-products resulting from the hydrolysis of

triglycerides (Figure 3-a). In fact, both oleic acid **Hp1** and a mix of glycerides **Hp2** have significantly slowed down the reaction rate, reaching respectively a maximum of 20 and 22 wt% of PMP **2/3** after 30 min. A similar behavior was observed with products originating from the fatty esters oxidation (Figure 3-b). Peroxidized methyl oleate **Dp2** allowed to reach the equilibrium in 20 min. and only 17 wt% of PMP were obtained in the presence of *n*-nonanal **Dp1**. Lastly, no detrimental effect occurred with standolie **Dp3** as additive.

The bleaching operation is part of the refining process of crude oils to achieve high quality oil standards for edible applications. The properties of bleaching earths allow for the removal of numerous impurities including oxidation products, resulting in lower peroxide and anisidine values. Extracted from quarries, these natural earths with high adsorption capacity are abundant, cheap and commercially available,^[16] which make them particularly suited to an industrial application of the Ru-catalyzed SM of methyl oleate. The expected beneficial effect of bleaching earth was confirmed after filtration of the refined oil (94% of methyl oleate) on Tonsil Supreme 110FF®^[16b] (100 wt%), as the equilibrium could be reached with 0.01 mol% of Ru-6a (Table 1, entry 1). Nevertheless, 5% of methyl oleate was lost during the filtration process and we therefore considered performing the metathesis reaction in presence of the bleaching earth.

Entry	Pre-treatment [a]	Ru-6 (mol%)	Conv. (%) ^[c]	2/3 (wt%) ^[d]	TON ^[e]	TON _p ^[g]
1	Method A	0.0100	89.5	47	8750	4850
2	Method B	0.0015	83.5	48	53000	32300

Table 1. Chemical pre-treatments of refined MO (Z)-1 with bleaching earths prior SM catalyzed by Ru-6a. [a] Method A: Filtration of (Z)-1 on Tonsil 110FF (100 wt%); Method B: (Z)-1, Tonsil 110FF (10 wt%), 50 °C, 15 min. [b] Ru-6a (x mol%), 50 °C, neat, 15 min. [c] Conversions of (Z)-1, monitored by GC (see ESI for details) [d] Percentage per weight of 2/3 in the crude, determined by GC (see ESI). [e] TON=conv.x(initial moles of (Z)-1/moles of catalyst)/100. [f] productive TON of 2+3=(moles of 2 + 3)/(moles of catalyst).

Interestingly, the treatment of the oil with 10 wt% of tonsil 110FF over 15 min followed by the introduction of Ru-6a led the metathesis reaction to readily reach the equilibrium even with a catalyst loading as low as 0.0015 mol% (15 ppm) and a TON of 53000 (Table 1, entry 2). These improved results, prompted us to apply this methodology to a non-refined VHOSO oil containing 85% of methyl oleate (Radia 7072®),^[17] a ton-scale available raw material suitable for industrial scale-up.^[18] Nevertheless, probably due to an important level of peroxide detected in the starting material in comparison with the refined oil (28 vs 3.2 meq O₂/Kg, respectively),^[19] up to 0.02 mol% of catalyst was necessary to reach the equilibrium of the self-metathesis (Table 2, entry 1). Fortunately, a simple thermic heating at 185 °C under vacuum (10 mbar) over 2 hours followed by the treatment

with 10 wt% bleaching earth (50 °C, 15 min.) allowed to reach the equilibrium within 1 hour at extremely low 0.0005 mol% catalyst loading (5 ppm, entry 3). Taking into account its abrasive nature that may damage the stainless-steel reactor at pilot scale, we decided to further diminish the amount of the bleaching earth. The optimal conditions were later found by increasing the time contact between the sorbent and the starting material (up to 120 min). With 1 wt% of the bleaching earth, the equilibrium of metathesis was reached with an extremely low loading of Ru-6a (0.0005 mol%, entry 6).^[20] Remarkably, under these conditions, the catalyst remained active at 1 ppm loading, converting 65% of the non-refined MO (Z)-1 to achieve an impressive TON of 744000 and a related productive TON of 359000 (entry 7). This is the first time a catalytic system has exhibited such high performance in a self-metathesis reaction of methyl oleate.^[8]

Entry	Pre-treatment 1[a]	Tonsil 110FF (wt%) ^[b]	Ru-6 (mol%) ^[c]	time (min.)	Conv. (%) ^[d]	2/3 (wt%) ^[e]	TON ^[f]	TON _p ^[g]
1	none	none	0.06	15	90	43	1570	850
2	none	10	0.02	15	97	43	5060	2700
3	with	10	0.0005	60	88	43	202100	115400
4	with	3	0.001	60	89	43	102100	57400
5	with	1	0.002	60	90	43	51600	28500
6	with	1 (120 min.)	0.0005	60	90	43	172500	94700
7	with	1 (120 min.)	0.0001	60	65	27	744000	359000

Table 2. Optimization of bleaching earth pre-treatments towards non-refined MO (Z)-1 prior SM catalyzed by Ru-6a. [a] 185 °C, 10 mbar, 2 h. [b] Tonsil 110FF (y wt%), 50 °C, 15 min. [c] Ru-6a (x mol%), 50 °C, neat. [d] Conversions of (Z)-1, monitored by GC (see ESI for details). [e] Percentage per weight of 2/3 in the crude, determined by GC (see ESI). [f] TON=conv.x(initial moles of (Z)-1/moles of catalyst)/100. [g] productive TON of 2+3=(moles of 2 + 3)/(moles of catalyst).

Intrigued by this remarkable efficiency to trap poisons from the crude oil without any noticeable detrimental side effects on the catalytic activity, we decided to investigate the interaction between the bleaching earth and the ruthenium catalyst. Surprisingly, when Ru-6a (0.002 mol%) was pre-mixed with tonsil 110FF (1 wt%), no metathesis transformation of MO occurred (Scheme 3, a). A similar inactivity was also observed at higher catalyst loading (0.1 mol%). Moreover, the total lack of activity was confirmed in an attempt to perform the ring-closing metathesis (RCM) of 1,7-octadiene **4** (Scheme 3, b). As Tonsil 110FF is mainly composed by silica (75.5%),^[21] we suspected a rapid impregnation of the ruthenium catalyst, as depicted in scheme 3. Indeed, after dissolving Ru-6a in dichloromethane (picture A), the green color fully disappeared after the addition of the bleaching earth (10 wt%, picture B). The resulting colorless supernatant was then used in SM of (Z)-1 or RCM of **4** and showed no metathesis activity, attesting the complete impregnation of the catalyst with the tonsil. Moreover, the

impregnated catalyst was also inactive.^[22] On the other hand, when the tonsil 110FF is mixed with the non-refined oil prior the addition of the catalyst (picture C), the resulting supernatant remained green (picture D) and displayed good catalytic activity in metathesis of **4** (>99% within 5 min, see ESI for details). All these experiments showed that the bleaching earth is able to rapidly deactivate the ruthenium complex^[23] but becomes totally inert toward the catalyst after the adsorption of impurities contained in a non-ultra-pure oil.

Scheme 3. Deactivation of the Ru-6a catalyst by impregnation onto Tonsil 110FF bleaching earth.

We continued our optimization study by screening alternative commercially available sorbents (Figure 4). Introduced at 1 wt%, most of the sorbents allowed for modest catalytic activity with 20 ppm of Ru-6a. For instance, under our conditions, the use of magnesium silicate (magnisol® D60) which has been widely employed in oil pre-treatment^[12d] led to a low production of 14 wt% PMP **2/3**. Durcal 2, Trisyl or Flucat 22B showed better efficiency, but with up to 29 wt% of **2/3** in the best case. The optimal production of PMP **2/3** was obtained with bleaching earths Tonsil 110FF and 112FF as well as the less cost-attractive silica hydrogel trisyl 300. Therefore, we chose to pursue our study with the cheap Tonsil 110FF.

Figure 4. Screening of sorbents for the pretreatment of non-refined MO (Z)-1 prior SM catalyzed by Ru-6a. [a] Condition: 185 °C, 10 mbar, 2 h then sorbent (1 wt%), 50 °C, 15 min. [b] Condition: Ru-6a (0.002 mol%), 50 °C, neat, 1 h. [c] Percentage per weight of **2/3** in the crude, determined by GC (see ESI).

With this cost-effective and efficient pretreatment condition in hands, the SM of non-refined MO (Z)-1 was re-investigated with alternative commercially available complexes Ru-2,3 and Ru-5,6 (Figure 5). Under our condition, first generation catalysts bearing PCy₃ ligands (Ru-2a,3a) were totally inactive. While second generation complexes bearing the SIMes ligand (Ru-2b,3b) displayed poor activities to produce 13 to 15 wt% of PMP **2/3**, no reactivity was observed with Evonik catalyst Ru-3c bearing the unsaturated IMes ligand. On the other hand, phosphine-free complexes Ru-5,6 appeared more robust demonstrating relatively similar levels of efficiency (40 to 43 wt% of PMP **2/3**).

Figure 5. Screening of commercially available catalysts Ru-2-3 and Ru-5-6 in the SM of non-refined MO (Z)-1. [a] Conditions: 185 °C, 10 mbar, 2 h then sorbent (1 wt%), 50 °C, 2 h. [b] Conditions: Ru-catalyst (0.0015 mol%), 50 °C, neat, 1 h. [c] Percentage per weight of **2/3** in the crude, determined by GC (see ESI).

SIPr-M71 Ru-6a, which afforded the highest conversion, was selected for the scale-up development of the transformation (Table 3). The first attempt at 1 Kg scale was performed using 0.01 mol% of Ru-6a. After the thermic treatment, the non-refined MO was reacted with 1%wt of Tonsil 110FF at 50 °C. The media turned rapidly brown with a slight exothermic reaction (10 °C). After the addition of Ru-6a, the equilibrium was reached within 15 min with 83.5% conversion, affording PMP **2** and **3** in 39 wt% (entry 1). We next attempted the metathesis at 3 Kg scale with 0.0005 mol% of catalyst (5 ppm). The excellent conversion with a high TON of 189000 observed after 1 h attested for the robustness of the pretreatment and prompted us to perform a pilot-scale production (200kg). In a 300 L reactor, the addition of Tonsil 110FF, preceded by a thermic pretreatment that decreased the peroxide content from 18 to 0.09 meq O₂/Kg, allowed for an excellent olefin metathesis performance, as the equilibrium was reached within 15 min converting the non-refined MO (Z)-1 in 88% (entry 3, see the kinetic profile in ESI).^[24] Importantly, no evolution of the equilibrium was observed over 5 h leading to PMP **2** and **3** in 41 wt%. Therefore, a remarkable TON of 174000 was reached at the equilibrium, with a productive TON of 94900.

Entry	Scale-up	Ru-6a (mol%)	time (min.)	Conv. (%) ^[c]	2/3 (wt%) ^[d]	TON ^[e]	TON _p ^[f]
1	1 Kg	0.01	15	83.5	39	8300	4500
2	3 Kg	0.0005	60	88	42	189000	104300
3	200 Kg ^[g]	0.0005	300	88	41	174000	94900

Table 3. Scale-up development of SM of non-refined MO (Z)-1 catalyzed by Ru-6a. [a] Conditions: 185 °C, 10 mbar, 2 h then sorbent (1 wt%), 50 °C, 2 h. [b] Ru-6 (x mol%), 50 °C, neat. [c] Conversions of (Z)-1, monitored by GC (see ESI for details). [d] Percentage per weight of 2/3 in the crude, determined by GC (see ESI). [e] TON=conv.x(initial moles of (Z)-1/moles of catalyst)/100. [f] productive TON of 2+3=(moles of 2 + 3)/(moles of catalyst). [g] Tonsil 110FF reacted with MO over 2 h 30.

In conclusion, an efficient, practical and cost-effective pretreatment through the use of cheap bleaching earths was proposed to mediate the ruthenium-catalyzed self-metathesis of non-refined methyl oleate (Z)-1 (85% of purity) derived from Very High Oleic Sunflower Oils at very low catalyst loading. The use of commercially available bleaching earth Tonsil 110FF® (1 wt%) combined with a thermic pretreatment enabled to trap all poisons presents in the raw material without any requirement of filtration prior the metathesis. With a catalytic loading of 0.0005 mol% (5 ppm) of SIPr-M71 pre-catalyst, non-refined (Z)-1 was converted in up to 90% within 1 hour at 50 °C under neat conditions and the expected primary metathesis products, the 9-octadecene 2 and the dimethyl-9-octadecenoate 3, were produced in 43 wt%. Importantly, the catalytic system remained active as low as 1 ppm enabling reaching 65% conversion with the highest TON of 744000. The robustness of the catalytic process has proven to be also efficient at pilot-scale (up to 200 Kg) with an impressive productive TON of 94900. Application of this efficient and scalable pre-treatment protocol is currently investigated to other valuable and challenging metathesis transformations of non-refined vegetable oils, such as alkenolysis of fatty ester/acids.^[2]

Acknowledgements

This work was supported by the Agence Nationale de la Recherche (ANR-12-CD21-0002 CFLOW-OM). MM thanks Rennes Métropole and the Région-Bretagne (SAD n°8734) for their financial supports concerning the development of Ru-based complexes. We are grateful to the ANRT and Oléon (Grant to I.C. and J.A., CIFRE n° 2012/0182), the CNRS and the ENSCR.

Keywords: Olefin Metathesis • ruthenium • oleochemicals • bleaching earths • pilot production

[1] Report of the United Nations Conference on Environmental Development, Rio de Janeiro (Brazil) <http://www.un.org/esa/sustdev>, Accessed 1992

- [2] 179 millions tons per year have been produced in 2015/2016, see: J. Spekrijse, J. P. M. Sanders, J. H. Bitter, E. L. Scott, *ChemSusChem* **2017**, *10*, 470 and references cited therein.
- [3] Selected comprehensive books on olefin metathesis: (a) R. H. Grubbs, A. G. Wenzel, D. J. O'Leary, E. Khosravi, (Eds.) *Handbook of Metathesis*, 2nd Edition; Wiley-VCH: Weinheim, Germany, 2015; (b) K. Grela (Ed.), *Olefin Metathesis: Theory and Practice*, Wiley-VCH: Weinheim, Germany, 2014.
- [4] For a review, see: A. Rybak, P. A. Fokou, M. A. R. Meier, *Eur. J. Lip. Sci. Technol.* **2008**, *110*, 797.
- [5] (a) Y.-M. Choo, K.-E. Ooi, I.-H. Ooi, D. D. H. Tan, *J Am Oil Chem Soc.* **1996**, *73*, 333; (b) W. Keim, *Angew. Chem. Int. Ed.* **2013**, *52*, 12492.
- [6] M. A. R. Meir, J. O. Metzger, U. S. Schubert, *Chem. Soc. Rev.*, **2007**, *36*, 1788. See also ref. 4.
- [7] M. B. Dinger, J. C. Mol, *Adv. Synth. Catal.* **2002**, *344*, 671.
- [8] R. Kadyrov, C. Azap, S. Weidlich, D. Wolf, *Top. Catal.* **2012**, *55*, 538.
- [9] See for instance: M. Rouen, P. Queval, E. Borré, L. Falivene, A. Poater, M. Berthod, F. Hugues, L. Cavallo, O. Baslé, H. Olivier-Bourbigou, M. Mauduit, *ACS Catal.* **2016**, *6*, 7970.
- [10] Extra-pure methyl oleate (>99%) is commercialized by Aldrich (62€/5 g).
- [11] S. Chikkali, S. Mecking, *Angew. Chem. Int. Ed.* **2012**, *51*, 5802.
- [12] (a) D. W. Lemke, K. D. Uptain, F. Amore, T. Abraham, *PCT Int. Appl. WO* 2009/020667; (b) Z. Lysenko, B. R. Maughon, J. Bicerano, K. A. Burdett, C. P. Christenson, C. H. Cummins, M. L. Dettloff, J. M. Maher, A. K. Schrock, P. J. Thomas, R. D. Varjian, J. E. White, *PCT Int. Appl. WO* 2003/093215; (c) S. A. Cohen, D. R. Anderson, Z. Wang, T. M. Champagne, T. A. Ung, *US Pat.* 2014/0275681; (d) K. D. Uptain, C. Tanger, H. Kaido, *PCT Int. Appl. WO* 2009/020665.
- [13] M71-SIPr is commercialized by Umicore company (www.umicore.com). For the related publication, see: H. Clavier, F. Caijo, E. Borré, D. Rix, F. Boeda, S. P. Nolan, M. Mauduit, *Eur. J. Org. Chem.* **2009**, *25*, 4254.
- [14] The other compounds were identified as saturated and mono- or poly-unsaturated fatty methyl esters: C14:0 (0.02 wt.%); C14:1 (0.01 wt.%); C16:0 (2.7 wt.%); C16:1 (0.03 wt.%); C18:0 (1.3 wt.%); C18:2 (1.6 wt.%); C22:0 (0.06 wt.%) and C22:1 (0.2 wt.%).
- [15] The kinetic profile of the reaction showed that the equilibrium was reached within 4 min (See ESI for details).
- [16] (a) For more information, see: *Oils&Fats International*, June 2016, 32(5), pp 26-31; (b) Tonsil® bleaching earths are commercialized by Clariant.
- [17] Radia 7072® is commercialized by Oleon company. The other compounds were identified as saturated and mono- or poly-unsaturated fatty methyl esters: C16:0 (3.4 wt.%); C16:1 (0.1 wt.%); C18:0 (1.8 wt.%); C18:2 (3.1 wt.%); C18:3 (1.8 wt.%); C20:0 (0.2 wt.%) C22:0 (0.3 wt.%) and C22:1 (0.7 wt.%).
- [18] The recrystallization process leading to a better quality of raw material (i.e. 94%) appeared too costly and inappropriate at industrial scale.
- [19] The peroxide value is defined as the amount of peroxide oxygen per 1 kilogram of oil and is determined by measuring the amount of iodine which is formed by the reaction of peroxides with iodide ion.
- [20] Composition of the crude after filtration: (Z/E)-2 (15.7 wt.%), (Z/E)-3 (27.2 wt.%), (E)-1 (26.6 wt.%), (Z)-1 (8.2 wt.%).
- [21] Composition of Tonsil Supreme 110FF® (average values): SiO₂ (75.5%), Al₂O₃ (12%), Fe₂O₃ (2.4%), CaO (0.4%), MgO (1.4%), Na₂O (0.3%), K₂O (1%).
- [22] SIPr-M71 impregnated onto amorphous silica has proved to be quite efficient in olefin metathesis, see: H. Nasrallah, D. Dragoe, C. Magnier, C. Crévisy, M. Mauduit, E. Schulz, *ChemCatChem* **2015**, *7*, 2494.
- [23] (a) Additional experiments were done showing the detrimental effect of a mixture of metallic oxides (Fe₂O₃, CaO and MgO) towards the Ru-catalyst (see ESI for details). For previous studies reporting the catalyst decomposition by oxidation, see: (b) D. W. Knight, I. R. Morgan, A. J. Proctor, *Tetrahedron Lett.* **2010**, *51*, 638. (c) M. Mauduit, F. Caijo, C. Crévisy, *PCT Int. Appl. WO* 2009/0805403; (d) A. Jana, K. Grela, *Org. Lett.* **2017**, *19*, 520.
- [24] Composition of the crude after filtration: (Z/E)-2 (15.8 wt.%); (Z/E)-3 (25.4 wt.%); (E)-1 (38.5 wt.%); (Z)-1 (10.2 wt.%).

Jessica Allard,^[a,b] Idriss Curbet,^[a]
 Guillaume Chollet,^[c] Fabien Tripoteau,^[d]
 Sophie Sambou,^[b] Frédéric Caijo,^[d]
 Yann Raoul,^[b] Christophe Crévisy,^[a]
 Olivier Baslé^[a] and Marc Mauduit^[a] *

An efficient and cost-effective pretreatment was proposed to mediate the Ru-catalyzed self-metathesis of non-refined methyl oleate (Z)-1 (85%) derived from *Very High Oleic Sunflower Oils* (VHOSO). The use of bleaching earths (Tonsil 110FF, 1 wt%) combined with a thermic pretreatment enabled metathesis under neat conditions with a catalytic loading as low as 0.0001 mol% (1 ppm) and impressive turnover number (TON) of 744000. The robust catalytic process has proven to be efficient at pilot scale (200 Kg) with a remarkable productive TON (94900) for expected primary metathesis products 9-octadecene **2** and dimethyl-9-octadecenoate **3**.

Bleaching Earths as Powerful Additives for Ru-Catalyzed Self-Metathesis of Non-Refined Methyl Oleate at Pilot Scale.