Investigation of $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses for efficient $2\ \mu\text{m}$ mid-infrared laser materials

Aoju Dou, Lingling Shen, Ning Wang, Yangjian Cai, Muzhi Cai, Yanyan Guo, Feifei Huang, Ying Tian, Shiqing Xu, Junjie Zhang

► To cite this version:

Aoju Dou, Lingling Shen, Ning Wang, Yangjian Cai, Muzhi Cai, et al.. Investigation of $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses for efficient $2\ \mu\text{m}$ mid-infrared laser materials. Applied Physics B - Laser and Optics, 2018, 124 (5), pp.86. 10.1007/s00340-018-6957-2 . hal-01807076

HAL Id: hal-01807076

<https://hal-univ-rennes1.archives-ouvertes.fr/hal-01807076>

Submitted on 4 Oct 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Investigation on $\text{Tm}^{3+}/\text{Yb}^{3+}$ codoped germanate-tellurite glasses for efficient $2\mu\text{m}$ mid-infrared laser materials

Aoju Dou¹, Lingling Shen¹, Ning Wang¹, Yangjian Cai¹, Muzhi Cai^{1,2}, Yanyan Guo³,

Feifei Huang¹, Ying Tian¹, Shiqing Xu¹, Junjie Zhang^{*1}

¹College of Materials Science and Engineering, China Jiliang University, Hangzhou 310018, P.R

China

²Laboratory of Glasses and Ceramics, Institute of Chemical Science UMR CNRS 6226, University

of Rennes 1, 35042 Rennes, France

³Collage of Materials Science and Engineering, Changchun University of Science and Technology,

Changchun, 130022, P.R China

Abstract:

The $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses with good thermal properties were prepared. Based on the absorption spectra and the Judd-Ofelt theory, the J-O intensity parameters (Ω_t), radiative transition probability (276.78s^{-1}), fluorescence lifetime (3.89ms) and absorption and emission cross sections ($\sigma_e = 1.35 \times 10^{-20} \text{cm}^2$) were calculated. The $\sim 2\mu\text{m}$ mid-infrared emission resulting from the $^3\text{F}_4 \rightarrow ^3\text{H}_6$ transition of Tm^{3+} sensitized by Yb^{3+} has been observed pumped by 980nm LD. Besides, the energy transfer mechanism between Yb^{3+} and Tm^{3+} was thoroughly discussed. Meanwhile, the measured $\sim 2\mu\text{m}$ emission lifetime of $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped glass can reach as high as 2.38ms. The above results showed that $\text{Tm}^{3+}/\text{Yb}^{3+}$

* Corresponding author at: China Jiliang University, No. 555 Xueyuan Road, Jiangnan Xiasha District, Hangzhou 310018, China. Tel: +86138 1649 4960; Fax: +0571-87676298.
E-mail address: jjzhang@cjl.u.edu.cn(J.J. Zhang)

co-doping glass could be expected to be a promising material to achieve high efficient $\sim 2\mu\text{m}$ lasing with a 980nm LD pumping.

1. Introduction

Over the past several years, increasing efforts have been made to develop $\sim 2.0\mu\text{m}$ fiber lasers driven by their wide applications such as remote sensing, laser surgery, environmental monitoring, and eye-safe light detection and ranging (LIDAR) [1-4].

Among the rare earth ions, Tm^{3+} and Ho^{3+} are well-known for the generation of $\sim 2.0\mu\text{m}$ emission, due to Tm^{3+} : $^3\text{F}_4 \rightarrow ^3\text{H}_6$ and Ho^{3+} : $^5\text{I}_7 \rightarrow ^5\text{I}_8$ transitions, respectively. In comparison with Ho^{3+} , Tm^{3+} is of special interests for its unsurpassed advantages, such as broad emission about 800nm suitable for tunable lasers [5] and high quantum efficiency be beneficial from the cross relaxation energy transfer ($^3\text{H}_4 + ^3\text{H}_6 \rightarrow ^3\text{F}_4 + ^3\text{F}_4$) [6]. What is more, the $^3\text{F}_4$ level of Tm^{3+} can be populated using sensitizer ions such as Yb^{3+} and Er^{3+} [7, 8]. Yb^{3+} ion can be used as a sensitizer and it can be pumped by a more powerful and relatively inexpensive laser diode (LD) at 980nm. Because fast diffusion among the Yb^{3+} ions can enhance the efficiency of the nonresonant energy transfer from Yb^{3+} to Tm^{3+} ($^2\text{F}_{5/2} + ^3\text{H}_6 \rightarrow ^2\text{F}_{7/2} + ^3\text{H}_5$). Yb^{3+} has a high absorption cross section and can effectively absorb excitation of commercial 980nm LD emission, and then transfer energy to Tm^{3+} ($^3\text{H}_5$ level) via non-resonant energy transfer process.

In order to research luminescence properties of rare-earth ions, it is very significant to select glass hosts for researchers. Since the first successfully Tm^{3+} doped silica fiber laser was demonstrated in 1988 by Southampton [9]. In 1999, Stuart

D. Jackson et al. proposed a theoretical model that describes the ion-pair dynamics relevant to the Tm-doped silica system, which can deduce equations for the steady-state intracavity photon density and for the steady-state population densities of the isolated and paired ions [10]. In 2009, Peter F. Moulton et al. used a piece of 25- μm -diameter and 0.08 numerical aperture (NA) core thulium-doped silica fiber to derive single mode laser output of the output powers of 300W and the slope efficiency as high as 64.5% for launched pump power [11]. Various host materials including fluoride [12], tellurite [13], germanate [6] and silicate glasses [14] have been successfully applied to achieve $\sim 2.0\mu\text{m}$ fiber lasers with different efficiency. The obvious defects of silicate glasses are the low rare-earth solubility and high phonon energy. The fluoride glasses have the drawbacks of inferior mechanical and chemical properties. Germanate glasses have been intensively studied as promising candidates in mid-infrared optical applications, and high energy laser system [15-17]. Particularly, one system, Germanate-tellurite (GT) glass which has been practically applied in large infrared (IR) windows, because of the excellent combinations of superior IR transparency, comparatively low phonon energy, high rare-earth solubility, and good mechanical characteristics [18]. Tellurite glass has attracted a great deal of interest not only for its relatively lower maximum phonon energy ($\sim 760\text{cm}^{-1}$) among all the oxide glasses, but also for the improvement in chemical and mechanical stability as well as the high refractive index, excellent infrared transmission [19]. Compared with germanate glass ($\sim 900\text{cm}^{-1}$) [20], tellurite glass ($\sim 760\text{cm}^{-1}$) [19] has much lower phonon energy, which is favorable for $2\mu\text{m}$ emission and that is helpful to reduce the

multi-phonon relaxation rate for Tm^{3+} : $^3\text{F}_4 \rightarrow ^3\text{H}_6$ transition. However, tellurite glass has lower glass transition temperature ($\sim 350^\circ\text{C}$) than germanate glass ($\sim 600^\circ\text{C}$). Thus, tellurite glass has poor thermal stability to resist thermal damage at high pumping power. On the contrast, the thermal stability, chemical durability, resistance to thermal damage of germanate glass are superior. Therefore, germanate-tellurite glass combines the advantages from both germanate and tellurite glasses, i.e., good thermal stability, chemical durability, lower phonon energy, high rare earth solubility and high transparency in a wide wavelength range [21,22]. These features render germanate-tellurite glass as an ideal host for mid-infrared laser material. To the best of our knowledge, the fluorescence corresponding to the $^3\text{F}_4 \rightarrow ^3\text{H}_6$ transitions of the Tm^{3+} has been under-reported sensitized by Yb^{3+} in germanate-tellurite glasses [23-25].

In this work, we report $\text{Tm}^{3+}/\text{Yb}^{3+}$ codoped germanate-tellurite glasses for generating emission in the $\sim 2.0\mu\text{m}$ wavelength band. Spectroscopic properties of Tm^{3+} and energy transfer mechanism between Tm^{3+} and Yb^{3+} ions were discussed in detail. Energy transfer microscopic parameters were calculated based on absorption spectra. Furthermore, the thermal properties are investigated and Judd-Ofelt intensity parameters have been determined to evaluate the radiative properties. In this paper, the lifetime and gain spectra have also been discussed. The results could verify that the $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses could be potential materials for mid-infrared lasers.

2. Experiment

2.1. Material synthesis

The sample glasses were prepared by traditional melt-quenching method with using high-purity chemicals (99%-99.99+%). The investigated glasses of molar compositions: $80(\text{GeO}_2+\text{TeO}_2)-(19.5-y)(\text{K}_2\text{CO}_3+\text{Nb}_2\text{O}_5+\text{La}_2\text{O}_3)-x\text{Yb}_2\text{O}_3-y\text{Tm}_2\text{O}_3$ ($x=0.5$; $y=0.1, 0.25, 0.4, 0.5$ and $x=0$; $y=0.1$) were placed in Al_2O_3 crucible and heated with a SiC-resistance electric furnace at 1200°C for 25min. The melts were then poured onto a preheated stainless mold, followed by annealing at 530°C for 5h to relinquish the inner stresses. Then it was allowed to cool slowly to room temperature. The cooled samples had been cut and polished to the size of $20\times 20\times 1.5\text{mm}^3$ carefully, prepared for the optical property measurements.

2.2. Performance measurements

In this paper, the refractive index (1.73) and density (4.27g/cm^3) of $0.25\text{Tm}^{3+}/0.5\text{Yb}^{3+}$ co-doped sample were tested by prism minimum deviation method and Archimedes principle using distilled water as an immersion liquid. The maximum phonon energy of present germanate-tellurite glass is $\sim 785\text{cm}^{-1}$. The maximum phonon energy ($\sim 785\text{cm}^{-1}$) is less than tellurite glasses ($\sim 900\text{cm}^{-1}$) [16]. The characteristic temperatures of glass transition (T_g), onset crystallization peak (T_x) and top crystallization (T_p) were performed with 10K/min using the NETZSCH DTA 404 PC differential scanning calorimeter. Fluorescence spectra of the samples in the range of $1500\text{-}2400\text{nm}$ were measured by a liquid-nitrogen-cooled PbS detector using a

980nm laser diode (LD) as an excitation source. The absorption spectra measurements were performed by PerkinElmer Lambda 900 UV/VIS/NIR double beam spectrophotometer (Waltham, MA) in the range from 300 to 2100nm. The lifetime decay curves were measured and shown by TDS 3012C type Digital Phosphor Oscilloscope (100MHz, 1.25GS/S). For different samples, they were tested under the same experimental conditions. In addition, all the test results were carried out at room temperature.

3. Results and discussions

3.1. Thermal stability analysis

To correctly evaluate the thermal properties of the glasses, as shown in Fig.1, the DSC measurement of sample glasses were displayed. The figures of T_g , T_x , and T_p are 538°C, 726°C, and 750°C, respectively. T_g is a significant factor for laser glasses. The transition temperature (T_g) of the samples (538°C) is higher than those of bismuth (269°C) [26], tellurite (354°C) [27], tellurite(300°C) [13], germanate (526°C) [28] and fluoride glasses (332°C) [29]. The higher T_g is generally considered to possess better thermal properties to resist thermal damage at high pumping intensities. The ΔT ($T_x - T_g$) can usually be used to evaluate the thermal properties of glasses. A bigger ΔT reveals that the glass possesses an excellent thermal ability against the nucleation and crystallization as well. From Table 1, it is obvious that ΔT is 188°C, which is significantly larger than those of bismuthate (67°C) [26], tellurite (141°C) [27], germanate (129°C) [28] and fluoride glasses (76°C) [29], which reveals that

germanate-tellurite glasses could be potential materials for mid-infrared lasers. The above results indicate that germanate-tellurite glasses have better thermal performance in this paper. Hence, the prepared germanate-tellurite glasses have good anti-crystallization properties and could be selected as potential laser material.

Fig.1. DSC curves of germanate-tellurite glass.

Table 1. The glass transition temperature (T_g), onset crystallization temperature (T_x), temperature of crystallization peak(T_p), thermal stability parameters ΔT in various glass hosts.

Glass samples	$T_g(^{\circ}\text{C})$	$T_x(^{\circ}\text{C})$	$T_p(^{\circ}\text{C})$	ΔT	References
GT	538	726	750	188	This work
Germanate	526	747	769	129	[28]
Tellurite	354	511	527	141	[27]
Bismuthate	269	336	358	67	[26]
Fluoride	332	408	426	76	[29]

3.2. Absorption spectra and J-O analysis

As shown in Fig.2, absorption spectra of 0.25Tm^{3+} , 0.5Yb^{3+} single doped and $0.25\text{Tm}^{3+}/0.5\text{Yb}^{3+}$ co-doped glass samples of thickness of 1.5mm is depicted in the wavelength range of 300-1750nm. For single Tm^{3+} doped the sample, in the range from 300 to 1750nm, It could be discerned five absorption bands centered at around 468、684、791、1208 and 1713nm, which correspond to the transitions from the $^3\text{H}_6$ ground state to excited levels $^1\text{G}_4$, $^3\text{F}_{2,3}$, $^3\text{H}_4$, $^3\text{H}_5$ and $^3\text{F}_4$, respectively, according to the absorption spectrum of Tm^{3+} single doped germanate glass. The shapes and the peak positions of each transition in Tm^{3+} single doped germanate-tellurite glasses nearly do not change when compared with the $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses and are very similar to those in other Tm^{3+} -doped glasses [30]. The phenomenon could be explained by the reason that the Tm^{3+} ions are

homogeneously incorporated into the glass network without clustering and any changes in the local ligand field [31]. In this paper, the 980nm LD is used as the pumping source. As we already know, the center of absorption peak of Yb^{3+} ions at 976nm is indeed more intense than all the absorption peaks of Tm^{3+} . The radiation wavelength of high power commercial 980nm LD can be matched with 976nm absorption peak of Yb^{3+} ions, showing that codoping with Yb^{3+} and Tm^{3+} is an efficient approach to enhance $\sim 1.8\mu\text{m}$ emission from Tm^{3+} [32,33].

Fig.2. Absorption spectra of Tm^{3+} , Yb^{3+} single doped and $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses.

The Judd-Ofelt (J-O) theory [34,35] plays a significant role in analyzing the spectroscopic properties (radiative lifetimes, intensity parameters Ω_t ($t=2, 4, 6$), spontaneous emission probabilities and so on) for rare earth ions doped glasses.

From Table 2, it compares the Judd-Ofelt parameters of Tm^{3+} ions in germanate, tellurite and bismuthate glasses. The Ω_2 parameter is intensively dependent on local

environment of the rare earth ions. The value of Ω_2 ($4.45 \times 10^{-20} \text{ cm}^2$) of Tm^{3+} is relatively large, which is higher than those of silicate ($3.70 \times 10^{-20} \text{ cm}^2$) [36], tellurite ($3.30 \times 10^{-20} \text{ cm}^2$) [37] glasses. On the one hand, it is straightly related to the symmetry of rare earth ions with ligand formation. On the other hand, the polarization of the local structure and the covalent nature of the chemical bonds result in the formation of rare earth ions with ligands. A large field strength is mainly attributed to a high polarizability of oxygen at the rare earth site. For the crystal field parameter, the value of Ω_2 might also be affected by the asymmetry of the rare earth sites. The Ω_2 is an important factor to obtain good spectral properties of the host materials. From Table 2, the value of Ω_6 is larger than silicate glasses ($0.60 \times 10^{-20} \text{ cm}^2$) [36], but smaller than tellurite ($1.28 \times 10^{-20} \text{ cm}^2$) [37] and germanate ($1.92 \times 10^{-20} \text{ cm}^2$) [38] glasses. At the same time, comparison with Ω_2 , Ω_6 doesn't depend on the environment but is more dependent on the overlap integrals of the 4f and 5d orbits [39].

Table 2. Comparison of J-O intensity parameters of Tm^{3+} ions in various glass hosts.

Glass	Ω_2	Ω_4	Ω_6	Reference
	$\times 10^{-20} \text{ cm}^2$)			
GTT	4.45	0.84	0.93	This work
Germanate	8.13	2.32	1.92	[38]
Silica	3.70	2.30	0.60	[36]
Tellurite	3.30	2.38	1.28	[37]
Bismuthate	6.51	2.11	1.52	[40]

From the Table 3, full understanding of the radiation characteristics of the prepared glasses, the radiative lifetimes (τ_{rad}), spontaneous transition probabilities (A_{rad}) and fluorescence branching ratios (β) were calculated. The radiative transition probability (A_{rad}) of $\text{Tm}^{3+}:^3\text{F}_4 \rightarrow ^3\text{H}_6$ transition is calculated to be 276.78s^{-1} . The higher spontaneous radiative transition probability provides larger opportunity to achieve better laser action, so the prepared glasses could be a promising candidate for mid-infrared laser [41]. It is known from other papers that the radiative transition probability (A_{rad}) of Tm^{3+} in sample is higher than those of tellurite and germanate glass [42,43]. We can see that the radiative lifetime of $^3\text{F}_4 \rightarrow ^3\text{H}_6$ transition is as long as 3.89ms, which is longer than that of tellurite (1.64ms) and germanate (0.859ms) glass [42,43]. The high efficient $\sim 2\mu\text{m}$ radiations can be achieved in the prepared glass.

Table 3. The spontaneous emission probabilities, branching ratios and radiative lifetimes of Tm^{3+} in the samples.

Transition	Final state	S_{ed} (10^{-20} cm^2)	$A_{\text{ed}} (\text{s}^{-1})$	$A_{\text{md}} (\text{s}^{-1})$	β	τ_{rad} (ms)
$^3\text{F}_4$	$^3\text{H}_6$	3.353	276.780	0	1	3.89
$^3\text{H}_5$	$^3\text{H}_6$	1.266	224.027	77.898	98.57%	3.26
	$^3\text{F}_4$	0.561	4.386		1.43%	
$^3\text{H}_4$	$^3\text{H}_6$	1.588	1240.053		90.58%	0.73
	$^3\text{F}_4$	0.862	99.750		7.29%	
	$^3\text{H}_5$	0.474	15.134	14.009	2.13%	
	$^3\text{H}_6$	1.048	1635.344		74.58%	0.46
$^3\text{F}_3$	$^3\text{F}_4$	0.169	57.322	93.308	6.87%	
	$^3\text{H}_5$	3.089	403.103		18.38%	
	$^3\text{H}_4$	0.939	3.741		0.17%	
	$^3\text{H}_6$	0.241	634.031		36.14%	0.57
$^3\text{F}_2$	$^3\text{F}_4$	1.356	874.099		49.82%	
	$^3\text{H}_5$	0.792	217.764		12.41%	
	$^3\text{H}_4$	1.610	28.417		1.62%	
	$^3\text{F}_3$	0.080	0.046	0.155	0.01%	
	$^3\text{H}_6$	0.279	1032.915		46.20%	0.45
	$^3\text{F}_4$	0.089	125.596		5.62%	
$^1\text{G}_4$	$^3\text{H}_5$	0.874	743.923		33.27%	
	$^3\text{H}_4$	1.119	275.795		12.34%	
	$^3\text{F}_3$	0.422	47.050		2.10%	
	$^3\text{F}_2$	0.148	10.439		0.47%	

3.3. Emission spectra and cross section

In the past studies [44], the energy transfer process between Yb^{3+} and Tm^{3+} is recognized by researchers, and the efficiency of the process is very high. As shown in Fig.3.(a), with the increase of Tm^{3+} concentration, the $\text{Tm}^{3+}:\sim 1.8\mu\text{m}$ emission is also enhanced as well. And the fluorescence spectra of $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glass pumped by 980nm LD is displayed. From Fig.3.(b), we can find that there is no fluorescence when Tm^{3+} singly doped in germanate-tellurite

glasses. With the assistance of Yb^{3+} ions, the $\sim 1.8\mu\text{m}$ emission peak of $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses are excited by 980nm LD. This confirms that the lack of Tm^{3+} absorption band near 976nm and the existence of energy transfer from Yb^{3+} to Tm^{3+} . In addition, with the increase of Tm^{3+} ions concentration, the fluorescence intensities of $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped glass samples increases initially, and then rapidly decreases. When the concentration of Tm^{3+} is 0.25mol%, the intensity of fluorescence emission reaches the maximum in these four sets of glass samples. So the optimum concentration of Tm^{3+} is 0.25mol%. The reason is that the energy transfer probability between $\text{Yb}^{3+}:^2\text{F}_{5/2}$ and $\text{Tm}^{3+}:^3\text{H}_5$ ions is enhanced. Subsequently, this emission intensity decreases gradually with the increase of Tm^{3+} ions concentration, because of the concentration quenching [45]. Therefore, the optimum concentration ratio between Tm^{3+} ions and Yb^{3+} ions is 1:2, the results can show that the $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses could be potential materials for mid-infrared lasers.

Fig.3.(a).Emission spectra of $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses; **(b).**

Emission spectra of Tm^{3+} doped and $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses.

Furthermore, emission cross section is an important parameter to estimate the possibility for achieving laser action. According to the above measured absorption spectra, the absorption cross section can be expressed as Beer–Lambert equation

$$\sigma_{abs} = \frac{2.303}{N \times l} OD(\lambda) \quad (1)$$

where N is the density of rare-earth ion (ions/cm³), l is the thickness of the polished sample glass, $OD(\lambda)$ is the optical density, the value of the optical density is equal to the spectra intensity.

$$\sigma_{em} = \frac{\lambda^4 \cdot A_{rad}}{8\pi c n^2} \times \frac{\lambda I(\lambda)}{\int \lambda I(\lambda) d\lambda} \quad (2)$$

where λ is the wavelength, A_{rad} is the spontaneous transition probability, $I(\lambda)$ is the emission intensity, c and n is the light speed in vacuum and refractive index, respectively.

As shown in figure Fig.4(a), the values of emission and absorption cross sections of Yb³⁺ are 0.87×10⁻²⁰cm² and 0.59×10⁻²⁰cm² in the sample glasses, respectively. From Fig.4(b), the value of emission and absorption cross section of Tm³⁺ are 1.35×10⁻²⁰cm² and 0.56×10⁻²⁰cm² at 1.8μm, respectively. We can see that the emission cross section (1.35×10⁻²⁰cm²) of Tm³⁺ is larger than those of silicate (0.2×10⁻²⁰cm²) [46], tellurite (0.86 ×10⁻²⁰cm²) [42], tellurite (0.96 ×10⁻²⁰cm²) [13] and bismuthate glasses (0.71 ×10⁻²⁰cm²) [47]. For a laser material, in generally, the high stimulated emission cross section is helpful to increase the gain. A larger gain results in better amplification behavior.

Fig. 4.(a)Absorption and emission cross sections corresponding to Yb³⁺:

²F_{5/2}→²F_{7/2}.(b) Absorption and emission cross sections corresponding to Tm³⁺:

$$^3F_4 \rightarrow ^3H_6.$$

The process of energy transfer between Tm³⁺ and Yb³⁺ ions is presented in Fig.5. As shown in Fig.5, the efficient energy transfer between Tm³⁺ and Yb³⁺ can be obtained through the transfer of phonons, and a main energy transfer process in the Tm³⁺/Yb³⁺ co-doped germanate-tellurite glass has was shown. The Yb³⁺ is pumped by 980nm LD and excited from the ground state (²F_{7/2}) to the upper level (²F_{5/2}), following a energy transfer process from Yb³⁺:²F_{5/2} to Tm³⁺:³H₅ (ET: Yb³⁺:²F_{5/2}+Tm³⁺:³H₆→Yb³⁺:²F_{7/2}+Tm³⁺:³H₅). And the process is assisted by phonons. The Tm³⁺ ion in the ³H₅ level relaxes very quickly to the ³F₄ level, then particle is transferred from ³F₄ level to ³H₆ level. Yb³⁺ ion as a sensitizer can greatly improve upconversion efficiency through energy transfer (ET), which is due to strong absorption of Yb³⁺ ion around 980 nm when Tm³⁺/Yb³⁺-codoped glasses are excited by 980 nm laser. The simplified energy level diagram exhibit distinct the

upconversion centered at 476nm, 650nm and 689 nm which are assigned to the $^1G_4 \rightarrow ^3H_6$, $^1G_4 \rightarrow ^3F_4$ and $^3F_{2,3} \rightarrow ^3H_6$ transitions of Tm^{3+} ions, respectively.

The microscopic parameter based on the evaluation of the overlap integral between the absorption and emission cross sections can be obtained using the following equations:

$$C_{DA} = \frac{6cg_{low}^D}{(2\pi)^2 n^2 g_{up}^D} \sum_{m=0}^{\infty} e^{-\frac{2m+1}{2} \frac{S_0^m}{m!} (\bar{n}+1)} \int \sigma_{em}^D(\lambda_m^+) \sigma_{abs}^A(\lambda) d\lambda \quad (3)$$

The g_{low}^D and g_{up}^D are the degeneracies of the respective lower and upper levels of the donor, respectively. $\bar{n} = 1/(e^{\hbar\omega_0/KT} - 1)$ is the average occupancy of the phonon mode at T. S_0 is Huang-Rhys factor.

The Table 4 has listed the energy transfer microscopic parameters of Tm^{3+}/Yb^{3+} co-doped germanate-tellurite glass. It's clearly shown that effective energy transfer takes place between Tm^{3+} and Yb^{3+} ions. As shown in Table 4, the energy transfer coefficient between $Yb^{3+}:^2F_{5/2}$ level and $Tm^{3+}:^3H_5$ level can be as high as $1.3826 \times 10^{-40} cm^6/s$. It is worth mentioning that the above energy transfer process is non-resonant and mainly assisted by one phonon (39.076%), two phonons (27.785%) and three phonons (1.696%). This circumstance mainly results from low phonon energy of germanate-tellurite glass. Besides, with increasing Tm^{3+} concentration, the energy transfer process can difficultly happen from $Yb^{3+}:^2F_{5/2}$ to $Tm^{3+}:^3H_5$. As shown in Fig.6, the decay curves can confirm this process. Hence, it is very important for mid-infrared materials to select suitable Tm^{3+} concentration.

Fig.5. Simplified energy level diagram of the Tm³⁺/Yb³⁺ co-doped system.

Table 4. Energy transfer parameters between Tm³⁺ and Yb³⁺ in glass sample

Energy transfer	N(number of phonons)(%phonon assisted)				Coefficient(cm ⁶ /s)
Yb ³⁺ (² F _{5/2})→Tm ³⁺ (³ H ₅)	0	1	2	3	1.3826×10 ⁻⁴⁰
	30.708	39.076	27.785	1.696	

3.4. Fluorescence lifetimes and gain coefficient

As shown in Fig.6, the 1.8μm highest lifetime (2.38ms) of Tm³⁺/Yb³⁺ co-doped germanate-tellurite glasses sample is obtained, and is significantly larger than those of silicate (1.42ms) [48] and germanate (0.36ms) glass [49]. The lifetime of Tm³⁺/Yb³⁺ in co-doped is longer than that in Tm³⁺ single doped germanate-tellurite glass. It indicates that there is an effective energy transfer between Tm³⁺ and Yb³⁺. We can see that the lifetime of ³F₄ level decrease gradually with increasing Tm³⁺ concentration. The reduced lifetime isn't beneficial for upconversion process. The decreased

upconversion process contributes to population aggregation of $\text{Tm}^{3+}{}^3\text{F}_4$ and might enhance $\text{Tm}^{3+}{}^3\text{H}_5 \rightarrow {}^3\text{F}_4$. Here the stronger upconversion process is due in part to the excited state absorption (ESA), while the excited state absorption process reduces the ${}^3\text{F}_4$ level number of particles, which is detrimental to the $1.8\mu\text{m}$ lifetime. Therefore, the decrease in the conversion process is beneficial to the $1.8\mu\text{m}$ lifetime of Tm^{3+} . In addition, the relatively long lifetime generally enhances the luminous efficiency of glasses and it generally reduces the laser oscillation threshold. Hence, the emission lifetimes (2.38ms) indicate that $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glass is a promising materials for $\sim 2.0\mu\text{m}$ fiber laser.

Besides, in order to further evaluate the performance of the samples, the fluorescence quantum efficiency has been estimated from the lifetime values by the following equation.

$$\eta = \frac{\tau}{\tau_{rad}} \times 100\% \quad (4)$$

where τ is the measured fluorescence lifetime of the sample ($0.5\text{Tm}^{3+}/0.1\text{Yb}^{3+}$), and τ_{rad} is the theoretical lifetime the sample ($0.5\text{Tm}^{3+}/0.1\text{Yb}^{3+}$). The measured ${}^3\text{F}_4$ lifetime (2.38ms) for Tm^{3+} is shorter than the calculated lifetime (3.89ms), which is due to non-radiative quenching. It can be found that the fluorescence quantum efficiency is high as 61.18%, which is higher than that of silicate glass (13.0%) [50]. Therefore, $\text{Tm}^{3+}/\text{Yb}^{3+}$ codoped germanate-tellurite glass is a more promising material for improving the Tm^{3+} $2.0\mu\text{m}$ fiber laser performance.

Fig.6. Decay curve of Tm³⁺/Yb³⁺ co-doped germanate-tellurite glasses.

Another important parameter to evaluate the gain performances of prepared sample quantitatively is gain coefficient. In order to calculate the gain ability of Tm³⁺/Yb³⁺ co-doped germanate-tellurite glasses, the gain coefficient $G(\lambda, P)$ of Tm³⁺/Yb³⁺ co-doped germanate-tellurite glasses is calculated. The room temperature gain coefficient ($G(\lambda, P)$) can be simply denoted as

$$G(\lambda, P) = N \left[P \sigma_{em}(\lambda) - (1 - P) \sigma_{abs}(\lambda) \right] \quad (5)$$

where N is the doping concentration of the rare-earth ion, P is the population inversion.

Fig. 7. Gain coefficient of $\text{Tm}^{3+}: {}^3\text{F}_4 \rightarrow {}^3\text{H}_6$ transitions in germanate-tellurite glasses.

The Fig.7 shows the calculated gain coefficients of Tm^{3+} and Yb^{3+} transitions as the function of wavelength. The gain coefficients results are calculated by setting the P ranging from 0 to 1 in interval of 0.1. We can see that the gain coefficient is increasing as the value of P continues to increase. As shown in Fig.7, the maximum gain coefficients of Tm^{3+} reach 3.02cm^{-1} , furthermore the concentrations of Tm^{3+} and Yb^{3+} are 0.1mol% and 0.5mol%, respectively. Besides when the P is more than 0.4, the value $G(\lambda, P)$ of the $\text{Tm}^{3+}: {}^3\text{F}_4 \rightarrow {}^3\text{H}_6$ transitions becomes positive number. In addition when the P is less than 0.4, it becomes negative number. The above results show that $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped $\text{GeO}_2\text{-TeO}_2\text{-K}_2\text{CO}_3\text{-Nb}_2\text{O}_5\text{-La}_2\text{O}_3$ glass has high gain and low pumping threshold for the laser, and is an outstanding gain host material for $\sim 2\mu\text{m}$ mid-infrared laser.

4. Conclusions

In a word, efficient $\sim 1.8\mu\text{m}$ emissions have been achieved in $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses. The energy transfer process between Yb^{3+} and Tm^{3+} has been investigated in detail. The thermal stability, absorption and emission cross sections, lifetimes have been analyzed. Results indicated that Tm^{3+} in the prepared glasses had not only superior thermo-mechanical stability ($T_g = 538^\circ\text{C}$, $\Delta T = 188^\circ\text{C}$), but also large emission cross section ($1.35 \times 10^{-20} \text{cm}^2$). The measured lifetime of $\text{Tm}^{3+}/\text{Yb}^{3+}$ co-doped germanate-tellurite glasses is as high as 2.38ms. It also possesses superior gain performance for $\text{Tm}^{3+}: {}^3\text{F}_4 \rightarrow {}^3\text{H}_6$ and $\text{Yb}^{3+}: {}^2\text{F}_{5/2} \rightarrow {}^2\text{F}_{7/2}$ transitions. All of the results indicate that the prepared germanate-tellurite glass is a promising candidate for $\sim 2.0\mu\text{m}$ mid-infrared laser materials applications.

Acknowledgment

This research was financially supported by the Chinese National Natural Science Foundation (No.61775205, 61605192 and 51502022).

References

- [1] G. X Chen, Q. Y Zhang, G. F Yang, Z. H Jiang, Mid-Infrared Emission Characteristic and Energy Transfer of Ho³⁺-Doped Tellurite Glass Sensitized by Tm³⁺. *J.Fluoresc.* 17(3), 301-307 (2007)
- [2] F. Amzajerian, J. Geng, Q. Wang, T. Luo, Single-frequency narrow-linewidth Tm-doped fiber laser using silicate glass fiber. *Opt. Lett.* 34(22), 3493-3495 (2009)
- [3] Yuen H. Tsang, Ashraf F. El-Sherif, Terence A. King, Broadband and amplified spontaneous emission fibre source near 2.0 μm using resonant in-band pumping. *J.Mod.Opt.* 52(1), 109-118 (2005)
- [4] W. J. Zhang, Q. Y. Zhang, Q. J. Chen, Q. Qian, Z. M. Yang, J. R. Qiu, P. Huang, Y. S. Wang, Enhanced 2.0 μm emission and gain coefficient of transparent glass ceramic containing BaF₂: Ho³⁺, Tm³⁺ nanocrystals. *Opt. Express.* 17(23), 20952-20958 (2009)
- [5] S. Agger, J. H. Povlsen, and P. Varming, Single-frequency thulium-doped distributed-feedback fiber laser. *Opt. Lett.* 29(13), 1503–1505 (2004)
- [6] J. F. Wu, Z. D. Yao, J. Zong, S. B. Jiang, Highly efficient high-power thulium-doped germanate glass fiber laser. *Opt. Lett.* 32(6), 638-640 (2007)
- [7] S. F. León-Luis, J. Abreu-Afonso, J. Peña-Martínez, J. Méndez-Ramos, A. C. Yanes, J. del-Castillo, V. D. Rodríguez, Up-conversion and colour tuneability in Yb³⁺-Er³⁺-Tm³⁺ co-doped transparent nano-glass-ceramics. *J. Alloys Compd.* 479(1), 557-560 (2009)
- [8] D. Zhou, Z. Song, G. Chi, J. Qiu, NIR broadband luminescence and energy transfer in Er³⁺-Tm³⁺ co-doped tellurite glasses. *J. Alloys Compd.* 48(1), 881-884 (2009)
- [9] D. C. Hanna, I. M. Jauncey, R. M. Percival, I. R. Perry, R. G. Smart, P. J. Suni, J. E. Townsend, A. C. Tropper, Continuous-wave oscillation of a monomode thulium-doped fiber Laser. *Electron. Lett.* 24(19), 1222–1223 (1988)
- [10] S. D. Jackson and T.A. King, Dynamics of the output of heavily Tm-doped double-clad silica fiber lasers, *Opt. Lett.* 16(12), 2178-2189 (1999)
- [11] P. F. Moulton, Tm-Doped Fiber Lasers: Fundamentals and Power Scaling, *Journal of the selected topics in quantum electronics*, 15(1), 85-92 (2009)
- [12] R. M. Percival, D. Szebesta, S. T. Davey, Highly efficient and tunable operation of two colour Tm-doped fluoride fibre laser. *Electron. Lett.* 28(7), 671-673 (1992)
- [13] K. F. Li, G. Zhang, L. L. Hu, Watt-level $\sim 2.0 \mu\text{m}$ laser output in Tm³⁺ doped tungsten-tellurite glass double-cladding fiber. *Opt. Lett.* 35(24), 4136–4138 (2010)
- [14] Q. Wang, J. Geng, T. Luo, S. Jiang, Mode-locked 2.0 μm laser with highly thulium-doped silicate fiber. *Opt.Lett.* 34(23), 3616–3618 (2009)
- [15] J. F. Wu, Z. D. Yao, J. Zong, S. B. Jiang, Highly efficient high-power thulium-doped germanate glass fiber laser. *Opt. Lett.* 32(6), 638–640 (2007)
- [16] N. P. Barnes, B. M. Walsh, D. J. Reichle, R. J. DeYoung, S. B. Jiang, Tm: germanate fiber

- laser: tuning and Q-switching. *Appl. Phys. B.* 89(2-3), 299–304 (2007)
- [17] F. Fusari, A. A. Lagatsky, G. Jose, S. Calvez, A. Jha, M. D. Dawson, J. A. Gupta, W. Sibbett, C. T. Brown, Femtosecond mode-locked Tm^{3+} and $\text{Tm}^{3+}\text{-Ho}^{3+}$ doped 2.0 μm glass Lasers. *Opt. Express.* 18(21), 22090–22098 (2011)
- [18] R. Xu, M. Wang, Y. Tian, L. Hu, J. Zhang, 2.05 μm emission properties and energy transfer mechanism of germanate glass doped with Ho^{3+} , Tm^{3+} , and Er^{3+} . *J. Appl. Phys.* 109(5), 285 (2011)
- [19] Y. Y. Guo, M. Li, Y. Tian, R. R. Xu, L. L. Hu, J. J. Zhang. Enhanced 2.7 μm emission and energy transfer mechanism of $\text{Nd}^{3+}/\text{Er}^{3+}$ co-doped sodium tellurite glasses. *J. Appl. Phys.* 110(1), 013512-013516 (2011)
- [20] M. D. Di, L. F. Santos, A. C. Marques. Vibrational spectra and structure of alkali germanate glasses. *J. Non-Cryst. Solids.* 293, 394-401 (2001)
- [21] G. Monteiro, L. F. Santos, J. Pereira, R. M. Almeida, Optical and spectroscopic properties of germanotellurite glasses. *J. Non-Cryst. Solids.* 357(14), 2695-2701 (2011).
- [22] M. Jayasimhadri, E. J. Cho, K. W. Jang, H. S. Lee, S. I. Kim, Spectroscopic properties and Judd-Ofelt analysis of Sm^{3+} doped lead-germanate-tellurite glasses. *J. Phys. D: Appl. Phys.* 41(17), 175101-175104 (2008).
- [23] H. Lin, Y. Y. Zhang, E. Y. B. Pun, Fluorescence investigation of Ho^{3+} in Yb^{3+} sensitized mixed-alkali bismuth gallate glasses. *Spectrochim. Acta. Part A.* 71(4), 1547-1550 (2008)
- [24] L. Huang, S. Shen, A. Jha, Near infrared spectroscopic investigation of $\text{Tm}^{3+}\text{-Yb}^{3+}$ co-doped tellurite glasses. *J. Non-Cryst. Solids.* 345-346(20), 349-353 (2004)
- [25] D. Di Martino, L. F. Santos, A. C. Marques, R. M. Almeida, Vibrational spectra and structure of alkali germanate glasses. *J. Non-Cryst. Solids.* 293-295(1), 394-401 (2001)
- [26] E. R. Shaaban, M. Shapaan, Y. B. Saddeek, Structural and thermal stability criteria of $\text{Bi}_2\text{O}_3\text{-B}_2\text{O}_3$ glass. *J. Phys. Condens. Matter.* 20(20), 155108 (2008)
- [27] D. D. Chen, Q. Y. Zhang, G. F. Yang, Z. H. Jiang, Thermal stability and spectroscopic properties of Er^{3+} doped niobium tellurite glasses for broadband amplifiers. *Mater. Chem. Phys.* 90(1), 78-82 (2005)
- [28] T. Wei, F. Chen, Y. Tian, S. Xu, 1.53 μm emission properties in Er^{3+} doped Y_2O_3 and Nb_2O_5 modified germanate glasses for an optical amplifier. *J. Lumin.* 154(154), 41-45 (2014)
- [29] Y. Tian, R. Xu, L. Hu, J. Zhang, 2.7 μm fluorescence radiative dynamics and energy transfer between Er^{3+} and Tm^{3+} ions in fluoride glass under 800nm and 980nm excitation. *J. Quant Spectrosc Radiat Transf.* 113(1), 87-95 (2012)
- [30] A. A. El-Maaref, K. H. S. Shaaban, M. Abdelawwad, Y. B. Saddeek, Optical characterizations and Judd-Ofelt analysis of Dy^{3+} doped borosilicate glasses. *Opt. Mater.* 72, 169-176 (2017).
- [31] G. C. Ram, T. Narendrudu, S. Suresh, D. Krishna Rao, Investigation of luminescence and laser transition of Dy^{3+} ion in $\text{P}_2\text{O}_5\text{-PbO-Bi}_2\text{O}_3\text{-R}_2\text{O}_3$ ($\text{R}=\text{Al, Ga, In}$) glasses. *Opt. Mater.* 66, 189-196 (2017).
- [32] F. Huang, Y. Ma, W. Li, X. Liu, L. Hu, D. Chen, 2.7 μm emission of high thermally and chemically durable glasses based on AlF_3 . *Sci. Rep.* 4, 3607 (2014)

- [33] B. R. Judd, Optical Absorption Intensities of Rare-Earth Ions. *Phys. Rev.* 127(3), 750-761 (1962)
- [34] G.S.Ofelt, intensities of Crystal Spectra of Rare-earth Ions, *J. Chem. Phys.* 37, 511-520 (1962)
- [35] H.Sun, L. Zhang, L. Wen, M. Liao, J. Zhang, Effect of PbCl_2 addition on structure, OH^- content, and upconversion luminescence in $\text{Yb}^{3+}/\text{Er}^{3+}$ co-doped germanate glasses. *Appl. Phys. B.* 80(7), 881-888 (2005)
- [36] R. Cao, M. Cai, Y. Lu, Y. Tian, F. Huang, S. Xu, J. Zhang, $\text{Ho}^{3+}/\text{Yb}^{3+}$ codoped silicate glasses for 2 μm emission performances. *Appl. Opt.* 55(8), 2065-2070 (2016)
- [37] S. Xu, Z. Yang, S. Dai, G. Wang, L. Hu, Z. Jiang, Upconversion fluorescence spectroscopy of Er^{3+} doped lead oxyfluoride germanate glass. *Mater. Lett.* 58(6), 1026-1029 (2004)
- [38] R. Xu, Y. Tian, L. Hu, J. Zhang, Broadband 2 μm emission and energy-transfer properties of thulium-doped oxyfluoride germanate glass fiber. *Appl. Phys. B.* 104(4), 839-844 (2011)
- [39] K. Li, H. Fan, G. Zhang, G. Bai, S. Fan, J. Zhang, L. Hu, Broadband near-infrared emission in $\text{Er}^{3+}\text{-Tm}^{3+}$ co-doped bismuthate glasses. *J. Alloys Compd.* 509(6), 3070-3073 (2011)
- [40] E. R. Shaaban, M. Shapaan, and Y. B. Saddeek, Structural and thermal stability criteria of $\text{Bi}_2\text{O}_3\text{-B}_2\text{O}_3$ glasses. *J. Phys. Condens. Matter.* 20(20), 155108 (2008)
- [41] K. Dieckmann, *Laser Spectroscopy*[M], World Scientific Publishing Co Pte Ltd. 1, 10 (2008)
- [42] J. Yuan, W. C. Wang, D. D. Chen, M. Y. Peng, Q. Y. Zhang, Z. H. Jiang, Enhanced 1.8 μm emission in $\text{Yb}^{3+}/\text{Tm}^{3+}$ codoped tungsten tellurite glasses for a diode-pump 2.0 μm laser. *J. Non-Cryst. Solids.* 402(17), 223-230 (2014)
- [43] C. Zhu, X. Zhao, Z. Wang, H. Lin, Upconversion photon quantification in $\text{Tm}^{3+}/\text{Yb}^{3+}$ doped aluminum germanate glasses for waveguide-type irradiation light sources. *Optik.* 127(23), 11544-11552 (2016).
- [44] G. Bai, Y. Guo, Y. Tian, L. Hu, J. Zhang, Light emission at 2.0 μm from Ho-Tm-Yb doped silicate glasses. *Opt. Mater.* 33(8), 1316-1319 (2011)
- [45] Y. Guo, Y. Ma, F. Huang, Y. Peng, L. Zhang, J. Zhang, 2.7 μm emission properties of Er^{3+} doped tungsten-tellurite glass sensitized by Yb^{3+} ions. *Spectrochim. Acta.A.* 111(111), 150-153 (2013)
- [46] G. Bai, Y. Guo, Y. Tian, L. Hu, J. Zhang, Light emission at 2.0 μm from $\text{Ho}^{3+}\text{-Tm}^{3+}\text{-Yb}^{3+}$ doped silicate glasses. *Opt. Mater.* 33(8), 1316-1319 (2011)
- [47] K. Li, S. Fan, L. Zhang, Q. Zhang, J. Zhang, L. Hu, Spectroscopic properties of the 1.8 μm emission of $\text{Tm}^{3+}/\text{Yb}^{3+}$ codoped $\text{TeO}_2\text{-ZnO-Bi}_2\text{O}_3$ glasses with efficient energy transfer. *J. Non-Cryst. Solids.* 357(11-13), 2417-2420 (2011)
- [48] R. Cao, Y. Lu, Y. Tian, F. Huang, Y. Guo, S. Xu, J. Zhang, Mid-infrared luminescence and energy transfer of Tm^{3+} in silicate glasses by codoping with Yb^{3+} ions, *Opt. Laser Technol.* 94, 106-111 (2017).
- [49] Y. Tian, R. Xu, L. Hu, J. Zhang, Efficient 2 μm emission and energy transfer mechanism of Ho^{3+} doped barium gallium germanate glass sensitized by Tm^{3+} ions, *Appl. Phys. B.* 108(3), 597-602 (2012)

[50] X. Q. Liu, M. Li, X. Wang, F. F. Huang, L. L. Hu, D. P. Chen. ~2 μm Luminescence properties and nonradiative processes of Tm^{3+} in silicate glass. J. Lumin. 150, 40-45 (2014).