Enhanced electrical conductivity and photoconductive properties of Sn-doped Sb₂Se₃ crystals

S. Chen, X. Qiao, Z. Zheng, M. Cathelinaud, Hongli Ma, X. Fan, Xianghua Zhang

► To cite this version:

S. Chen, X. Qiao, Z. Zheng, M. Cathelinaud, Hongli Ma, et al.. Enhanced electrical conductivity and photoconductive properties of Sn-doped Sb₂Se₃ crystals. *Journal of Materials Chemistry C*, 2018, 6 (24), pp.6465-6470. 10.1039/c8tc01683f . hal-01835068

HAL Id: hal-01835068

<https://hal-univ-rennes1.archives-ouvertes.fr/hal-01835068>

Submitted on 3 Sep 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Enhanced electrical conductivity and photoconductive properties of Sn-doped Sb₂Se₃ crystals†

Shuo Chen,^{ab} Xvsheng Qiao,^a Zhuanghao Zheng,^b Michel Cathelinaud,^b Hongli Ma,^b Xianping Fan^{*a} and Xianghua Zhang^{*b}

Sb₂Se₃ is a highly interesting semiconductor with high absorption coefficient in the visible range and is composed of non-toxic and earth-abundant elements. To overcome the challenge of intrinsic low electrical conductivity of Sb₂Se₃ crystals, tin-doped (Sn_xSb_{1-x})₂Se₃ semiconductors ($x = 0.00, 0.03, 0.05, 0.07$ and 0.10) have been synthesized by a conventional melt-quenching method in a vacuum sealed silica tube. With increasing Sn doping concentration, the (Sn_xSb_{1-x})₂Se₃ crystals exhibited a great improvement in electrical conductivity by several orders of magnitude thanks to the great increase of carrier concentration reaching almost $2 \times 10^{16} \text{ cm}^{-3}$. Compared to undoped Sb₂Se₃, the dark current density of a representative (Sn_{0.10}Sb_{0.90})₂Se₃ increased by approximately 10 times and the photocurrent density with essentially visible illumination increased by approximately 14 times. In addition, the doped sample showed a faster, reversible and stable photoresponse. These excellent performances combined with a simple and easily scalable synthesis method pave the way for using this semiconductor for highly efficient photoelectric devices.

Introduction

Antimony selenide (Sb₂Se₃) is an important V-VI binary semiconductor with excellent photovoltaic, photoconducting, photocatalytic and thermoelectric properties.¹⁻⁶ It has a high absorption coefficient higher than 10^5 cm^{-1} in the visible region and an optimum bandgap width of around 1.1 eV for single junction solar cells. In addition, it is stable and nontoxic and composed of earth abundant elements. These properties make it a promising candidate for various important applications in diverse areas such as solar energy conversion, photo-detector technology, thermoelectric power generation, and opto-electronics in the near-infrared region.^{5,7-11}

Despite the important research efforts, the progress in application development is still limited. One major issue with Sb₂Se₃ is its intrinsic low electrical conductivity ($10^{-6} \Omega^{-1} \text{ m}^{-1}$, in the bulk state), which results in low thermoelectric power factor, low spectral response and low external quantum efficiency.^{12,13} A few studies to improve the electrical

conductivity of Sb₂Se₃ have been reported. For example, Choi *et al.* developed Sb₂Se₃ nanowires decorated with Ag₂Se nanoparticles, which increased the electrical conductivity of the Sb₂Se₃ nanowires.¹² Zhang *et al.* explained an interpenetrating iodine-doped-Sb₂Se₃/Cu₂GeSe₃ heterojunction network fabricated by controlling the crystallization of chalcogenide glass which can improve the photoelectric performance.¹⁴ Our previous work including the synthesis of hybrid nanorods with the Sb₂Se₃/AgSbSe₂ heterojunction structure also shows a higher electrical conductivity and photodetector performance.¹⁰ Despite these endeavors, the synthesis of Sb₂Se₃-based crystals with controllable electrical conductivity has been rarely reported and still needs further exploration.

Doping is an efficient way to tune the electrical and photo-electrical performances of semiconductors. It has been widely utilized in the semiconductor industry.¹⁵⁻¹⁷ For example, S-doped In₂Se₃ nanowires show a much higher conductivity and spectral responsivity to visible light than undoped In₂Se₃ nanowires.¹⁷ A small amount of Sn leads to a significant increase in the electrical conductivity and photoconductivity of the amorphous As₂Se₃ films.¹⁸ Herein, we demonstrate a conventional melt-quenching method to controllably synthesize high-quality and variably doped (Sn_xSb_{1-x})₂Se₃ semiconducting crystals with the Sn ratio x ranging from 0.00 to 0.10. By incorporating additional Sn atoms into the binary Sb₂Se₃, a significant improvement in the electrical conductivity and

^a State Key Laboratory of Silicon Materials, School of Materials Science and Engineering, Zhejiang University, Hangzhou, 310027, P. R. China.

E-mail: fanxp@zju.edu.cn

^b Univ Rennes, CNRS, ISCR UMR6226, 35000 Rennes, France.

E-mail: xzhang@univ-rennes1.fr

† Electronic supplementary information (ESI) available. See DOI: 10.1039/c8tc01683f

photoconductivity is observed. Moreover, the as-synthesized bulk samples with easy and relatively large-scale synthesis features show very interesting properties for fabricating Sb_2Se_3 -based photoelectric devices.

Experimental

Synthesis of $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals

A conventional melt-quenching method using high purity tin (99.99%), antimony (99.999%) and selenium (99.999%) as raw materials was used to synthesize $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals. A schematic illustration of the preparation process is shown in Fig. S1 (ESI†). At first, a mixture of 12 g of raw materials according to the chemical composition $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ (where $x = 0.00, 0.03, 0.05, 0.07$ and 0.10 , respectively) was loaded into a fully cleaned silica tube of 1 cm internal diameter. A vacuum trap that was placed in liquid nitrogen was used to condense any volatile products and also to improve the vacuum. The silica tube was sealed under a typical vacuum of around 10^{-5} mbar and then was placed in a rocking furnace. The mixture was heated to 700°C at a rate of $1.5^\circ\text{C min}^{-1}$ and held for about 8 hours to ensure complete melting and homogenization. Then it was cooled down to 650°C during 2 hours and subsequent quenching in water at room temperature. Finally, in order to reduce the stress generated from the thermal shock in the quenching process, the as-synthesized crystals were annealed at 350°C for 3 hours.

Characterization

X-ray diffraction (XRD) analysis was carried out using a PANalytical's X-ray diffractometer with a step width of 0.02° and a counting duration of 0.13 s per step. Scanning electron microscopy (SEM) images and the corresponding Energy Dispersive Spectrometer (EDS) elemental mappings were obtained using a JEOL JSM-7100F thermal field emission electron microscope equipped with an EDAX instrument. TEM, HRTEM and SAED images were obtained using a JEOL JEM-2100 field emission transmission electron microscope. The bulk sample was milled and then dissolved in chloroform before being placed on the surface of a copper grid for further TEM measurements. The quality and composition of the crystals were also analyzed by X-ray photoelectron spectroscopy (XPS, ESCALAB). Before electrical conductivity and photoconductivity measurements, the as-synthesized $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals were sliced into small discs with a thickness of about 2 mm also with surface polishing. Electrical resistivity and bulk carrier density were measured using a van der Pauw Ecopia HMS-3000 Hall Measurement System (Ecopia Corporation, Anyang, South Korea). The temperature-dependent resistivity was measured by the conventional four-probe method in the temperature range of 300–400 K. To characterize the photoelectric performance, the photo-electro-chemical (PEC) measurement has been carried out using the classical 3-electrode method, where Ag/AgCl in saturated KCl was used as the reference electrode, Pt-wire as the counter electrode and our sample as the working

electrode. Additionally, to prepare the working electrode, the as-synthesized bulk $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals were sliced into small discs with a diameter of 10 mm and a thickness of about 2 mm, and then the surface was finely polished and cleaned. After this, silver paint was homogeneously applied on one face of the disc-like sample, acting as the back contact, which was connected by a copper wire and then covered with a layer of epoxy resin to be isolated from the electrolyte during the PEC test. Then these electrodes were immersed into the electrolyte ($0.5 \text{ mol L}^{-1} \text{ LiClO}_4$ solution), and a white light tungsten halogen lamp with controllable light intensities was used as the light source. A mechanical chopper was used to obtain chopped light and an Autolab Metrohm potentiostat was used to record the current-voltage characteristics.

Results and discussion

Fig. 1a shows the XRD patterns of the as-synthesized $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ polycrystalline semiconductors ($x = 0.00, 0.03, 0.05, 0.07$ and 0.10) acquired on sliced and polished disc-like samples, which all exhibit prominent peaks in agreement with the JCPDS standard card (15-0861) of the orthorhombic phase of Sb_2Se_3 without a second phase, indicating the absence of any detectable impurity. The absence of multiple sets of peaks also indicates that the $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals do not contain a second crystalline phase after Sn doping. Then the XRD patterns of the corresponding powdered samples obtained by grinding the bulk crystals into fine powders can be indexed to the same crystalline phase, as shown in Fig. 1b, suggesting that the crystallization process takes place uniformly inside the bulk sample and is not restricted to the surface. The relative peak intensity is different between the powder and the bulk because the preferential orientation in the bulk is destroyed during the grinding of the powders. It is noted that further

Fig. 1 (a) XRD patterns of the bulk $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals ($x = 0.00, 0.03, 0.05, 0.07$ and 0.10). (b) XRD patterns of the powdered $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ samples. (c) Lattice constants a , b and c derived from powder XRD peaks, plotted as a function of Sn doping concentration (x value). (d) XPS spectrum of Sn-3d for the $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals ($x = 0.00$ and 0.10).

increase of Sn doping concentration will lead to additional diffraction peaks corresponding to orthorhombic $\text{Sn}_2\text{Sb}_4\text{Se}_8$ (JCPDS Card No. 36-1206), indicating the existence of the second phase (Fig. S2, ESI[†]). The lattice parameters a , b and c were determined by refining the diffraction patterns through a Rietveld method implemented in the FULLPROF program,¹⁹ which show a slight increase upon increasing the Sn doping concentration (Fig. 1c). This can be attributed to the small difference in the atomic radius between Sb (0.160 nm) and Sn (0.158 nm). And this slight difference satisfies the criterion for substitution solubility proposed by Hume-Rothery who pointed out that an extensive solid solubility of one metal in another only occurs if the diameter of the atoms differs by less than 15%.²⁰ Furthermore, the calculated unit cell volume of the $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals gradually increases from 545.23 Å³ ($x = 0.00$) to 546.53 Å³ ($x = 0.10$), and this increase is known to occur due to doping.²¹ Fig. 1d shows the XPS spectrum of Sn-3d, compared to the pure Sb_2Se_3 . Two obvious peaks located at 494.7 and 486.2 eV from $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$ crystals indicate the existence of Sn, further confirming the successful doping.

The $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals' ($x = 0.00, 0.03, 0.05, 0.07$ and 0.10) morphology of the freshly fractured surface observed by SEM is shown in Fig. S3 (ESI[†]). All the samples consisted of large crystals with a layered-like structure and clear strips, indicating a preferential orientation. According to the theoretical and experimental studies, bulk Sb_2Se_3 has an orthorhombic crystal structure and is composed of 1D ribbon-like $(\text{Sb}_4\text{Se}_6)_n$ units stacking together *via* van der Waals interactions.²² Its preferential growth is indeed determined intrinsically by the anisotropic Sb-Se atom chain or the layer structure.^{7,10} To further investigate the doping nature and also the grain size of the $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals, the finely polished disk-like samples were etched chemically by 1 mol L⁻¹ NaOH solution for 20 min at room temperature. As shown in Fig. 2a, the Sb_2Se_3 crystal consists of some big micron-sized grains. Fig. 2b shows a representative etched microstructure of the $(\text{Sn}_{0.05}\text{Sb}_{0.95})_2\text{Se}_3$ crystal; the grains are clearly shown with an average size of approximately 15 μm. In addition, compositional spatial distribution was determined by EDS elemental mappings marked with Sn, Sb and Se, which reveals a uniform distribution of Sb and Se within the crystal. And a few Sn-rich zones between the grain boundaries can also be observed after chemical etching. Then for the $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$ crystal with a higher Sn doping concentration, more obvious Sn-rich regions can be observed, as shown in Fig. 2c. This could be explained by phase separation, which is reasonable to occur, the minor Sn-rich phase solidifies first, and then is pushed to the grain boundaries upon freezing of the major phase. To further reveal the elemental composition of these Sn-rich regions, EDS analysis has been performed. Fig. 2d shows the EDS spectra recorded from two different positions (Point 1 in Fig. 2b and Point 2 in Fig. 2c); the atomic ratio of Sn:Sb:Se is 14.54:23.74:61.72 and 15.39:22.22:62.39 for Point 1 and Point 2, respectively. It is noted that the composition analysis of these Sn-rich regions performed on different $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals show quite similar results, close to the ratio of 2:4:8 for $\text{Sn}_2\text{Sb}_4\text{Se}_8$, which is also consistent with the XRD results.

Fig. 2 SEM images of (a) the Sb_2Se_3 crystal, (b) the $(\text{Sn}_{0.05}\text{Sb}_{0.95})_2\text{Se}_3$ crystal and (c) the $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$ crystal surface with chemical etching by NaOH solution and following the corresponding EDS elemental mappings of Sn, Sb and Se. (d) EDS spectra recorded from two different positions (Point 1 in (b) and Point 2 in (c)).

Fig. 3 (a) TEM image of the representative $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$ crystal. SAED pattern (b) and the corresponding HRTEM image (c) from the rectangle marked area in (a). (d) EDS spectrum.

Fig. 3a shows the TEM image of an isolated particle milled from the $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$ crystal. The selected area electron diffraction (SAED) pattern (Fig. 3b) from the red marked area (in Fig. 3a) is a periodic spot pattern, suggesting its highly crystalline nature. Fig. 3c shows the corresponding HRTEM image with obvious lattice fringes associated with the (020) planes (d -spacing of 0.591 nm) of the orthorhombic phase Sb_2Se_3 . Then the EDS spectrum (Fig. 3d) exhibits strong Sb

and Se peaks, and also an observable Sn peak located at 3.44 eV, indicating the successful Sn doping in this crystal.

Fig. 4a shows the electrical resistivity of the as-synthesized $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals with different x values. It can be seen that the pure Sb_2Se_3 exhibits extremely high resistivity. With Sn doping, a significant decrease of resistivity is observed, and the decrease is almost exponential with the x value. The temperature dependent electrical conductivity (σ) in the temperature (T) range of 300–400 K has also been studied. As shown in Fig. 4b, the plots of $\ln \sigma$ versus $1/T$ indicate that the electrical conductivity increases with increasing temperature for all samples, confirming semiconductor characteristics of these samples. Moreover, the conductivity exhibits single activation energy in the temperature range of measurement, according to the Arrhenius equation:

$$\sigma = \sigma_0 \exp(-\Delta E/kT) \quad (1)$$

where σ_0 is the pre-exponential factor, ΔE is the activation energy and k is the Boltzmann constant.²³ Thus the thermal activation energy ΔE can be calculated from the slope, while the intercept on the y -axis gives the σ_0 value. Then the bulk carrier density and the doping type were determined by Hall measurements. All the electrical parameters of $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals are summarized in Table 1. It is obvious that the room temperature electrical conductivity shows an increase with several orders of magnitude after Sn doping, accompanied by a synchronous increase of bulk carrier density, which change from $1.44 \times 10^{11} \text{ cm}^{-3}$ ($x = 0.00$) to $1.94 \times 10^{16} \text{ cm}^{-3}$ ($x = 0.10$). Importantly, such a great improvement will provide a bright future for widening applications of Sb_2Se_3 . Since the activation energy varies inversely with the charge carrier density, Sn incorporation in this system should theoretically lead to a decrease of activation energy, which is consistent with the calculated ΔE values. The pre-exponential factor has a close relationship with the defect or impurities in the crystals, Sn doping into Sb_2Se_3 also creates a compositional and configuration disorder, leading to an increase in the localized state density, which is an important factor for the change of σ_0 values. Table 1 also shows the conduction type of $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals; Sn incorporation has been found to result in P-type behavior, suggesting Sn substitution at the Sb site. Sn possesses one fewer valence electron than Sb, thus replacing Sb with Sn constitutes hole doping.²⁴

Fig. 4 (a) Electrical resistivity of $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals with different x values. (b) Temperature dependent electrical conductivity (σ) of $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals in the temperature (T) range 300–400 K.

Table 1 A summary of electrical conductivity (σ), bulk carrier density (n), pre-exponential factor (σ_0), activation energy (ΔE) and conduction type of $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals with varied x

x value	σ (S cm^{-1})	n (cm^{-3})	σ_0 (S cm^{-1})	ΔE (eV)	Conduction type
0.00	2.71×10^{-6}	1.44×10^{11}	1.31×10^3	0.52	N
0.03	1.30×10^{-3}	1.52×10^{15}	2.65×10^3	0.38	P
0.05	4.12×10^{-3}	3.59×10^{15}	9.96×10^2	0.32	P
0.07	9.65×10^{-3}	6.90×10^{15}	1.49×10^3	0.30	P
0.10	7.50×10^{-2}	1.94×10^{16}	3.48×10^2	0.22	P

Photoconductivity is a well-known property of semiconductors which describes the electrical conductivity changes with the incident radiation. The photoconductive characteristics of the semiconducting $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals are investigated here by using the classical 3-electrode photo-electro-chemical (PEC) measurements. A schematic illustration of this PEC measurement is shown in Fig. 5a. It is noted that with this 3-electrode technique which measures the generated and separated electron-hole pairs on the surface, it can eliminate the influence of the bulk resistance of the sample, facilitating therefore the comparison between different samples. Fig. 5b shows the current density versus voltage under chopped light using $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ ($x = 0.00, 0.03, 0.05, 0.07$ and 0.10) as the working electrode, respectively. It is obvious that both dark current and photocurrent density of pure Sb_2Se_3 are very weak, which can be explained by its intrinsic low conductivity and low carrier concentration. For Sn-doped crystals, a significant increase of current density is observed, and this increase is proportional to the Sn doping concentration. Up to $x = 0.10$, the dark current density increased approximately 10 times (from $-16 \mu\text{A cm}^{-2}$ to $-160 \mu\text{A cm}^{-2}$ at a bias voltage of -0.6 V) and the photocurrent density increased approximately 14 times

Fig. 5 (a) Schematic diagram of the 3-electrode photo-electro-chemical (PEC) measurement. (b) Current-voltage characteristics using $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals as working electrodes. (c) Dark current density and photocurrent densities at different power densities of the representative $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$ crystal. (d) Photocurrent densities measured as a function of incident light density at a bias voltage of -0.7 V .

(from $-18 \mu\text{A cm}^{-2}$ to $-250 \mu\text{A cm}^{-2}$ at -0.6 V). This improvement can be considered as an important step to promote Sb_2Se_3 -based semiconductors for application in high performance photoelectric devices. Fig. 5b also shows that the Sn-doped Sb_2Se_3 crystals are identified as p-type semiconductors, due to their photocurrent density increase with a negative bias, which is confirmed by the Hall measurement results. Then the light intensity dependence of current density is also investigated. As shown in Fig. 5c, using $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$ as an example, upon illumination, the current density is increased, and then it increases gradually with increasing light intensity. Additionally, current-voltage curves of $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ at other x values (0.00, 0.03, 0.05 and 0.07) are shown in Fig. S4 (ESI[†]), where similar phenomena were observed. All the samples show that the photocurrent strongly depends on the light intensity, which can be attributed to the change in photo-generated carriers. The corresponding photocurrent density as a function of light intensity is shown in Fig. 5d, and dependence can be described by the power law:

$$J_{\text{ph}} = AP^\theta \quad (2)$$

where J_{ph} represents the photocurrent density; P is the power density of the incident light; A is a constant at a specific wavelength; and θ is an exponent.^{25,26} The fitting curves showed that $\theta = 0.27, 0.52, 0.65, 0.60$ and 0.54 for x values of 0.00, 0.03, 0.05, 0.07 and 0.10, respectively. All these θ values are non-unity, indicating that some surface defects and carrier trapping at the localized states could result in a complex electron-hole non-radiative recombination process.⁴

To evaluate the stability and the response speed of the photocurrent, chronoamperometry measurements have been performed. Fig. 6a and b show two plots of the time-resolved PEC response using Sb_2Se_3 and $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$ as the working electrode, respectively. As shown in Fig. 6a, when the light is

on, the current density rapidly increases from $-10.75 \mu\text{A cm}^{-2}$ (dark condition) to $-12.25 \mu\text{A cm}^{-2}$ (with 22.51 mW cm^{-2} light illumination), and then sharply returns to its initial value as the light is turned off. This light response remains the same after multiple cycles, indicating the excellent reversibility and stability of this Sb_2Se_3 PEC electrode. Then a similar photoresponse can be seen for $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$, except for a larger photocurrent density in the latter case (Fig. 6b). When using the $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$ crystal as the working electrode, a huge photocurrent density spike before arriving at a steady value can also be observed, which was caused by recombination in the presence of surface states.²⁷ To extract the exact response time, one of the response periods is magnified, as shown in Fig. 6c and d, respectively. Under closer examination, the response time (τ_{on}) and the recovery time (τ_{off}) of the Sb_2Se_3 working electrode are 0.05 s and 0.07 s, respectively. For $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$, both values show a decrease in value to 0.03 s, which can be attributed to much more surface dangling bonds, high crystal quality and preferential orientation.^{28,29} It is worth noting that these short response times are comparable to the very good results of some reported high performance photodetectors,^{30,31} further conforming the high potential application of Sn-doped Sb_2Se_3 crystals as excellent photoelectric devices.

The optical absorption spectrum is one of the most effective tools for understanding and/or engineering the band structures of semiconductor materials. It is known that an appropriate band gap of the semiconductor plays a crucial role in fabricating high performance photoelectric devices. In this work, the optical absorption spectrum has been employed to characterize the as-synthesized $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals. And the absorption data were calculated from diffuse reflectance data using Kubelka-Munk equations: $F(R) = \alpha/\Lambda = (1 - R)^2/(2R)$, where R is the reflectance, α and Λ are the absorption and scattering coefficients, respectively.³² As shown in Fig. 7a, the onset of the absorption of Sb_2Se_3 crystals starts near 1200 nm, and a shift toward a longer wavelength is observed after Sn doping. The higher absorption efficiency for the doped crystals in the NIR range is interesting for broad spectrum applications. Fig. 7b shows a plot of $[F(R)h\nu]^2$ versus energy ($h\nu$); the direct band gap of Sb_2Se_3 is 1.17 eV, and then for the Sn-doped Sb_2Se_3 crystals, the band gap is similar and close to 1.10 eV. The dwindling band gaps of the doped $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals can be explained

Fig. 6 Time-resolved PEC photoresponse by using Sb_2Se_3 (a) and $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$ (b) as the working electrode, respectively. (c) Magnified plot of one response cycle in (a), and (d) one response cycle in (b), used to obtain the response time and the recovery time.

Fig. 7 (a) Optical absorption spectra (calculated from diffuse reflectance data) of the $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals ($x = 0.00, 0.03, 0.05, 0.07$ and 0.10) (b) a plot of $[F(R)h\nu]^2$ vs. energy, from which direct band gap was obtained.

by the cooperation of the Burstein–Moss shift and the renormalization effect. This mechanism exists in narrow band gap semiconductors with a specific doping level.^{33,34} Finally, it is worth noting that the band gap of the $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals is close to the best value for absorbing efficiently the solar spectrum, making them attractive candidates for photovoltaic application.

Conclusions

An effective melt-quenching method has been used to synthesize high-quality and variably doped $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals with the dopant Sn ratio x ranging from 0.00 to 0.10. The successful doping is verified by XRD, XPS and EDS results. With increasing Sn doping concentration, $(\text{Sn}_x\text{Sb}_{1-x})_2\text{Se}_3$ crystals exhibit an improvement of electrical conductivity with several orders of magnitude due to a much higher charge carrier concentration. Temperature dependent electrical conductivity displays a typical semiconductor characteristic and a decrease of activation energy is also confirmed with Sn incorporation. Sn-Doped Sb_2Se_3 crystals are identified as p-type semiconductors according to the photoconductive characteristics. Notably, compared to pure Sb_2Se_3 , the dark current density of a representative $(\text{Sn}_{0.10}\text{Sb}_{0.90})_2\text{Se}_3$ increased approximately 10 times and the photocurrent density increased approximately 14 times. In addition, it shows a short response/recovery time (0.03/0.03 s) and a reversible and stable photoresponse. Therefore, the Sn-doped Sb_2Se_3 crystals have an optimal band gap, (1.10 eV) which overlaps well with the solar spectrum, and excellent electrical conductivity and photoconductive properties, combined with their easy and relatively large-scale synthesis features. These properties confirm the high application potential of Sn-doped Sb_2Se_3 as highly efficient photoelectric devices.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The authors gratefully acknowledge support for this research from the Program for Innovative Research Team in the University of Ministry of Education of China (IRT13R54), the Fundamental Research Funds for the Central Universities (2016FZA4007) and the Zhejiang Provincial Natural Science Foundation of China (LY16E020003). We also thank the Chinese Scholarship Council and the Eiffel Excellence Scholarship Programme for financial support.

Notes and references

- 1 L. Wang, D. B. Li, K. Li, C. Chen, H. X. Deng, L. Gao, Y. Zhao, F. Jiang, L. Li, F. Huang, Y. He, H. Song, G. Niu and J. Tang, *Nat. Energy*, 2017, **2**, 17046.

- 2 G. X. Liang, X. H. Zhang, H. L. Ma, J. G. Hu, B. Fan, Z. K. Luo, Z. H. Zheng, J. T. Luo and P. Fan, *Sol. Energy Mater. Sol. Cells*, 2017, **160**, 257–262.
- 3 T. Zhai, M. Ye, L. Li, X. Fang, M. Liao, Y. Li, Y. Koide, Y. Bando and D. Golberg, *Adv. Mater.*, 2010, **22**, 4530–4533.
- 4 Y. Q. Liu, M. Zhang, F. X. Wang and G. B. Pan, *J. Mater. Chem. C*, 2014, **2**, 240–244.
- 5 T. Y. Ko, M. Shellaiah and K. W. Sun, *Sci. Rep.*, 2016, **6**, 35086.
- 6 N. Hu, M. A. Cheney, Y. Hanifehpour, S. W. Joo and B.-K. Min, *J. Nanomater.*, 2017, **2017**, 1–8.
- 7 Y. Zhou, L. Wang, S. Chen, S. Qin, X. Liu, J. Chen, D. J. Xue, M. Luo, Y. Cao, Y. Cheng, E. H. Sargent and J. Tang, *Nat. Photonics*, 2015, **9**, 409–415.
- 8 Y. Zhou, M. Leng, Z. Xia, J. Zhong, H. Song, X. Liu, B. Yang, J. Zhang, J. Chen, K. Zhou, J. Han, Y. Cheng and J. Tang, *Adv. Energy Mater.*, 2014, **4**, 1301846.
- 9 R. Huang, J. Zhang, F. Wei, L. Shi, T. Kong and G. Cheng, *Adv. Funct. Mater.*, 2014, **24**, 3581–3586.
- 10 S. Chen, X. Qiao, F. Wang, Q. Luo, X. Zhang, X. Wan, Y. Xu and X. Fan, *Nanoscale*, 2016, **8**, 2277–2283.
- 11 T. Zhai, L. Li, X. Wang, X. Fang, Y. Bando and D. Golberg, *Adv. Funct. Mater.*, 2010, **20**, 4233–4248.
- 12 D. Choi, Y. Jang, J. Lee, G. H. Jeong, D. Whang, S. W. Hwang, K. S. Cho and S. W. Kim, *Sci. Rep.*, 2014, **4**, 6714.
- 13 R. J. Mehta, C. Karthik, W. Jiang, B. Singh, Y. Shi, R. W. Siegel, T. Borca-Tasciuc and G. Ramanath, *Nano Lett.*, 2010, **10**, 4417–4422.
- 14 X. H. Zhang, Y. Xu, Q. H. Shen, B. Fan, X. S. Qiao, X. P. Fan, H. Yang, Q. Luo, L. Calvez, H. L. Ma, M. Cathelinaud and J. J. Simond, *J. Mater. Chem. A*, 2014, **2**, 17099–17106.
- 15 D. Kong, K. J. Koski, J. J. Cha, S. S. Hong and Y. Cui, *Nano Lett.*, 2013, **13**, 632–636.
- 16 W. Tian, C. Zhi, T. Zhai, S. Chen, X. Wang, M. Liao, D. Golberg and Y. Bando, *J. Mater. Chem.*, 2012, **22**, 17984.
- 17 T. Zhai, Y. Ma, L. Li, X. Fang, M. Liao, Y. Koide, J. Yao, Y. Bando and D. Golberg, *J. Mater. Chem.*, 2010, **20**, 6630.
- 18 M. S. Iovu, S. D. Shutov, V. I. Arkhipov and G. J. Adriaenssens, *J. Non-Cryst. Solids*, 2002, **299**, 1008–1012.
- 19 P. Barpanda, M. Ati, B. C. Melot, G. Rousse, J. N. Chotard, M. L. Doublet, M. T. Sougrati, S. A. Corr, J. C. Jumas and J. M. Tarascon, *Nat. Mater.*, 2011, **10**, 772–779.
- 20 C. H. Hu, M. H. Chiang, M. S. Hsieh, W. T. Lin, Y. S. Fu and T. F. Guo, *CrystEngComm*, 2014, **16**, 1786–1792.
- 21 A. Y. Shenouda and H. K. Liu, *J. Alloys Compd.*, 2009, **477**, 498–503.
- 22 H. Song, T. Li, J. Zhang, Y. Zhou, J. Luo, C. Chen, B. Yang, C. Ge, Y. Wu and J. Tang, *Adv. Mater.*, 2017, **29**, 1700441.
- 23 X. Liu, D. Zhang, H. Li, L. Li and H. Yuan, *Dalton Trans.*, 2017, **46**, 2479–2484.
- 24 S. R. Culp, J. W. Simonson, S. J. Poon, V. Ponnambalam, J. Edwards and T. M. Tritt, *Appl. Phys. Lett.*, 2008, **93**, 022105.
- 25 S. Chen, X. Liu, X. Qiao, X. Wan, K. Shehzad, X. Zhang, Y. Xu and X. Fan, *Small*, 2017, **13**, 1604033.
- 26 H. Zhang, X. Zhang, C. Liu, S. T. Lee and J. Jie, *ACS Nano*, 2016, **10**, 5113–5122.

- 1 27 R. L. Spray, K. J. McDonald and K. S. Choi, *J. Phys. Chem. C*, 2011, **115**, 3497–3506. 1
- 28 K. Zhang, T. Luo, H. Chen, Z. Lou and G. Shen, *J. Mater. Chem. C*, 2017, **5**, 3330–3335. 2
- 5 29 W. Zhou, Y. Peng, Y. Yin, Y. Zhou, Y. Zhang and D. Tang, *AIP Adv.*, 2014, **4**, 123005. 5
- 30 L. Zheng, K. Hu, F. Teng and X. Fang, *Small*, 2017, **13**, 1602448. 3
- 31 L. Li, L. Gu, Z. Lou, Z. Fan and G. Shen, *ACS Nano*, 2017, **11**, 4067–4076. 1
- 32 S. Wang and N. Ye, *J. Am. Chem. Soc.*, 2011, **133**, 11458–11461. 2
- 33 A. Walsh, J. L. F. Da Silva and S. H. Wei, *Phys. Rev. B: Condens. Matter Mater. Phys.*, 2008, **78**, 075211. 5
- 34 Z. M. Gibbs, A. LaLonde and G. J. Snyder, *New J. Phys.*, 2013, **15**, 075020. 3
- 10 10
- 15 15
- 20 20
- 25 25
- 30 30
- 35 35
- 40 40
- 45 45
- 50 50
- 55 55