Purification of Ge-As-Se ternary glasses for the development of high quality microstructured optical fibers

Marcello Meneghetti, Celine Caillaud, Radwan Chahal, Elodie Galdo, Laurent Brilland, Jean-Luc Adam, Johann Troles

► To cite this version:

Marcello Meneghetti, Celine Caillaud, Radwan Chahal, Elodie Galdo, Laurent Brilland, et al.. Purification of Ge-As-Se ternary glasses for the development of high quality microstructured optical fibers. *Journal of Non-Crystalline Solids*, 2019, 503-504, pp.84-88. 10.1016/j.jnoncrysol.2018.09.028 . hal-01944063

HAL Id: hal-01944063

<https://hal-univ-rennes1.archives-ouvertes.fr/hal-01944063>

Submitted on 4 Dec 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Purification of Ge-As-Se ternary glasses for the development of high quality microstructured optical fibers

Marcello Meneghetti¹, Celine Caillaud², Radwan Chahal², Elodie Galdo¹, Laurent Brilland², Jean-Luc Adam¹, Johann Troles¹

¹Univ Rennes, CNRS, ISCR - UMR 6226 F-35000 Rennes, France

²SelenOptics, 263 Avenue G^{al} Leclerc, 35042 Rennes, France

Abstract

The production of chalcogenide microstructured optical fibers with low optical losses, due to the broad transparency window of these glasses in the mid-IR, can allow for new breakthroughs in various research fields, e.g. new mid-IR laser sources and mid-IR spectroscopy. In this framework, high purity chalcogenide glasses are needed in order to minimize absorption losses. In this study, Ge₁₀As₂₂Se₆₈ samples were prepared using a double distillation method, using different combinations of chlorides and metals as getters for the physico-chemical elimination of carbon, oxygen and hydrogen impurities. Comparing the attenuation spectra of the different samples, the choice of the getters seems to be indeed a significant factor in the quality of the glass. A holey fiber has been realized by casting method using the best sample, showing that the method is suitable for this composition and that the attenuation before and after the casting are comparable.

Keywords: Chalcogenide glasses, Chemical synthesis methods, Microstructured optical fibers

1. Introduction

In the last twenty years the field of chalcogenide glasses has seen increasing interest, thanks to the broad transparency band they exhibit in the mid-infrared, up to wavelengths as high as 20 μm . This is an extremely interesting region of the light spectrum, and devices able to operate in it can have applications in many fields. In particular, chalcogenide fibers, that can have transmission in the 1 – 12 μm range [1], can be especially suitable for telecommunications, sensing, imaging and spectroscopy [2, 3]. Another important property of chalcogenides is showing one of the highest nonlinear refractive indices among glasses. For example, n_2 is around two orders of magnitude larger than the one of silica in sulfides and up to 1000 times larger than the one of silica in glasses based on heavier chalcogens (Se, Te). This high nonlinearity permits to observe nonlinear effects even in short fibers [4–7]. This allows for applications such as slow light (based on stimulated Brillouin scattering) [5], Raman amplification [8], 3R regeneration [8, 9], all-optical switching [10] and supercontinuum generation [11–13]. Of particular interest for nonlinear applications are microstructured optical fibers (MOFs), in which guiding properties are mainly defined by the d/Λ ratio (d : diameter of the holes, Λ : distance between the holes)[14]; in this kind of fiber the design can be altered to obtain large core single-mode, endlessly single-mode or polarization-maintaining fibers, as well as to enhance nonlinear properties and manage the chromatic dispersion[15]. Low losses chalcogenide MOFs obtained by using a casting method instead of the more typical stack-and-draw method have been demonstrated [7]. Among chalcogenide glasses, in this work Ge-As-Se ternary glasses were chosen, because of the good compromise between the position of the transparency window (which includes both the telecommunication C-band, around 1.55 μm ,

and mid-IR wavelengths), the nonlinear refractive index and the improved thermal and mechanical properties given by the addition of Germanium. In particular, the $\text{Ge}_{10}\text{As}_{22}\text{Se}_{68}$ composition has been demonstrated to be stable against crystallization and suitable to develop small core MOFs [16].

As it is well known, when looking towards fiber applications, the intrinsic losses of the material become a much more important matter (the large propagation length of the light magnifies their influence, with important consequences on the width of the transparency window and to the heating-related damage threshold). For this reason it's fundamental to minimize optical losses, and a first step toward this result is producing as pure as possible chalcogenide glasses. In the case of the Ge-As-Se system treated in this paper, this mainly translates in the removal of water and carbon particles as well as of oxygen and hydrogen pollution. Indeed, the presence of oxygen and hydrogen atoms induces intense absorption bands related to the vibrations of O – H, Se – H, and As – O bonds, which are centered at wavelengths overlapping with the material transparency window [17, 18]. In order to obtain high purity glasses, a method similar to the one described [19] was used: the syntheses have been performed in vacuum atmosphere in a sealed silica crucible, with the addition of getters, i.e. chemical compounds which purpose is to react with oxygen, carbon and hydrogen and give as byproducts either highly refractory or highly volatile compounds. This allows to use distillation to strongly decrease the amount of hydrogen and oxygen in the glass. The getters used in this physico-chemical process are usually halides for removing hydrogen [20] and metals for removing oxygen[21].

The purpose of this study is to proceed on the road to obtain further optimization of this synthesis procedure by comparing the efficacy of different getters in removing the aforementioned impurities, knowing that the most commonly used are TeCl_4 and Al or Mg [22–24], with the goal to improve the transmission of microstructured optical fibers based on high purity chalcogenide glasses. Other than the already mentioned common getters, we chose to use in this study also some novel ones: SeCl_4 , SbCl_3 , GaCl_3 , being chlorides of elements that can be included in the network of Ge-As-Se glasses without negative effects, and Zr, Ni, which high melting temperature oxides can be removed by distillation.

2. Experimental

We prepared different glasses by melt quenching technique in sealed tube with a double distillation to remove impurities: the charge and getters, placed in a sealed silica tube under high vacuum, were heated up to 800°C and subsequently quenched in water; after this step, they were annealed at a temperature just below T_g in order to reduce the internal stress. The charge was prepared with pure elements, nominally germanium 5N, arsenic 5N and selenium 5N, weighted and inserted in the tube in a glovebox, under inert atmosphere. During the melting of the charge, the reaction of the getters with the impurities occurs: the halides react with hydrogen and carbon, following reactions like the ones presented as an example below (only the initial and final states are shown, intermediate reaction steps are not well understood)

while the metals react with the oxygen in a way similar to the one shown below for the case of magnesium.

The resulting glass underwent a two step distillation, with temperature and duration of the steps in this procedure kept fixed along the different samples prepared for the comparison. The first one happens in an open setup, in connection with a pump actively removing gases (dynamic distillation). The second one is performed in a sealed setup, once again in high vacuum atmosphere (static distillation). A schematic of these processes can be found in Fig. 1. During the dynamic distillation the glass migrates from the hot zone, at a temperature of 600°C , to the cold zone. Metal oxides and residuals of silica from the crucible, being refractory, do not migrate, while water and hydrohalic acids, being volatile, are sucked into the liquid nitrogen cooled trap by the vacuum pump, and condensate there. The second step removes traces of metal oxides that could have remained inside the glass. After the distillations, the glass was melted, quenched and annealed again with the same procedure used for the first synthesis. This last step is fundamental to homogenize the material, which during the distillations was separated into compounds with different melting temperatures.

All the silica setups used were made of low OH content silica (< 3 ppm), and were etched with hydrofluoric acid before being used, in order to minimize the addition of further impurities to the glass, especially after the distillations. The glass composition before and after the distillation process was checked with energy dispersive spectroscopy (EDS) measurements. The variations in the stoichiometry, when measurable, were below 1%, and no leftover traces of getters were found in the glass after the distillation.

As for the different getters used in this comparison, TeCl_4 , SeCl_4 , SbCl_3 , GaCl_3 were chosen as halides, while as metals Mg, Al, Zr and Ni were used. The ratio between the mass of both getters (one halide and one metal for each sample) and the total mass of glass is kept fixed along all the samples. Specifically, each sample contains 2000 ppmw of hydrogen getter and 200 ppmw of oxygen getter. It is to be noticed that hydrogen getters used are all chlorides of elements well compatible with the chalcogenide glass network. Thanks to this and to the low concentration, those elements should not affect the optical properties in case they entered the glass during distillation.

In order to see the effect of the purification, the so-obtained glasses were then drawn in 125 μm fibers, the attenuation of which was measured by cut-back technique on a Bruker Tensor 37 FTIR spectrometer using an external liquid nitrogen cooled MCT detector. For each measurement two cut-backs were performed: one with a long part of fiber for the measurement of the low (background) attenuation and one with a short length of fiber for the measurement of the high (peaks) attenuation. The results of the two measurements were then combined into complete spectra. The error was estimated by comparison of repeated measurements on the same fiber, and like the experiment can be separated in two regimes: an error of about 0.1 dB/m for the background, where detection-related sources of error are dominant, and an error of about 5% for the peaks, where because of the short length of fiber random errors related to the cleaving of the fiber are dominant.

For each combination of getter studied, several syntheses were performed. Only the best results achieved will be shown in this study.

Holey preforms were then obtained by casting method [7] using some of the most promising glasses, and drawn into microstructured endlessly single mode fibers, which were characterized using once again FTIR spectrometry.

Fig. 1: Schematics of the dynamic (a) and static (b) distillation processes.

3. Results

In order to compare the effect of different hydrogen getters on the Se-H absorption peak (4.5 μm), a series of sample was prepared fixing Mg as the oxygen getter in combination with the different halides listed in Section 2. In a similar way, a second series was prepared using TeCl_4 as an hydrogen getter and the metals listed in Section 2, with the intention of studying the Ge-O and As-O peaks (7.9 μm and 8.9 μm respectively). Mg and TeCl_4 were chosen as fixed getters for the comparison because their use has already been documented on this composition [16]. The

measured losses in the transparency windows for the two series are visible in Fig. 2, together with an unpurified glass to show the huge improvements in terms of transmission given by the purification.

Fig. 2: Comparison between the attenuation spectra of Ge – As – Se fibers prepared using magnesium in combination with different hydrogen getters (a) and TeCl_4 in combination with different oxygen getters (b). In both graphs, an example of non purified glass is shown.

As it can be seen in Fig. 2.a, all of the halides but SbCl_3 appear to be quite efficient in suppressing the Se-H peak. From Fig. 2.b, it can be clearly seen that oxygen-wise Al, Mg and Zr seem to have similar effects, while Ni is not working as an oxygen getter. Indeed, the Ni containing sample has a Ge-O band comparable with the one of the non-purified glass. Interestingly, the choice of the metal also appears to have influence on the Se-H peak. The peaks at 2.9 μm and 6.3 μm appearing in the non-purified and Ni-containing samples are assigned to O-H and H_2O respectively. There are no visible carbon-related bands in any of the purified samples. Indeed, in our case carbon impurities are mainly particles, and they therefore induce scattering losses rather than absorption ones. The combination of TeCl_4 and magnesium, which has shown the best results in terms of attenuation, has been chosen as the most suitable for the realization by casting method [7] of a microstructured fiber, of which attenuation spectrum and cross section are visible in Fig. 3. This fiber has an diameter of 125 μm and a core diameter of 11 μm . The holes diameter (d) is 3.4 μm , while the pitch (Λ) is 7.2 μm , leading to a $\frac{d}{\Lambda}$ parameter of 0.47.

Fig. 3: Attenuation spectrum (a) and cross section (b) of a holey fiber obtained from the sample containing Mg and TeCl_4 .

4. Discussion

Looking at Fig. 2.a, TeCl_4 , SeCl_4 and GaCl_3 , reducing the intensity of the Se-H peak to a level of around 1.5 dB/m, seem to be considerably more efficient than SbCl_3 . In order to better understand the reason of this difference, a starting

point could be comparing the actual amount of chlorine ions introduced in the melt by the addition of the different halides, for which the mass was kept constant, under the assumption of full dissociation of all the compounds.

Table 1: Molar content of chlorine introduced in the melt by different getters.

Halide	Cl amount ($\text{mol} \cdot 10^{-3}$)
TeCl_4	1.75 ± 0.15
SeCl_4	2.1 ± 0.2
SbCl_3	1.6 ± 0.1
GaCl_3	2.0 ± 0.2

No relation between the theoretical moles of Cl and the efficiency appears to emerge from the values presented in Table 1, with TeCl_4 resulting to be the most efficient getter despite the relatively low total amount of chlorine it can introduce in the system. In accordance with the absence of this relation, increasing the mass of the getters didn't bring to better results. Also, comparing the standard Gibbs free energies of the different getters and of HCl in the range of temperatures [25–27] used during the synthesis, we see no trivial correlation between the stability of these chlorides and their efficiency; on the contrary, in a counterintuitive way the most stable compound, nominally GaCl_3 gives better results than the less stable SbCl_3 . This could be due to different elements in the melt acting as catalysts to favor the reaction in a way similar to the one suggested in [28]; the individuation of the actual reaction steps is far from the goals of this paper, but the fact that the partial elimination of Se – H bonds happens even without the addition of any metal to the melt (Fig. 4), a cooperative action of the two getters seems less probable with respect to the action of other glass or crucible components as catalysts.

Concerning the removal of oxygen, Fig. 2.b shows that magnesium, aluminum and zirconium efficiently suppress the Ge-O and As-O bands in the attenuation spectra of the respective samples. Nickel, on the other side, seems to be completely ineffective in this regard: as visible in Fig. 4, the spectrum of the Ni containing sample is almost perfectly superimposable with the one of a sample prepared with the same amount of TeCl_4 , but no oxygen getter. This is compatible with the Ellingham diagrams shown in Fig. 5.a, from which formation of NiO seem less favored than formation of GeO_2 , whereas formation of MgO and ZrO_2 appear to be both strongly favored against Germanium dioxide.

Fig. 4: Comparison between the attenuation spectra of a sample with Ni as a metal and a sample with no metal at all. In both samples TeCl_4 is used as hydrogen getter.

While the choice of the halide doesn't seem here to influence the content of oxides in a relevant way, when comparing the Se-H peaks of the samples prepared with different oxygen getters there is a significant difference. In this case too, the explanation from a reaction dynamics point of view is really complicated and would require deeper studies. Anyway, given the high absolute value of the formation ΔG of ternary compounds in the form $\text{M}_x\text{Si}_y\text{O}_z$, with M being a metal, shown in Fig. 5.b for Al, Zr and Mg, it is reasonable to suppose that the oxygen getters can interact with the silica crucible. This could cause the release of hydrogen from Si – O – H groups at the surface of the crucible,

therefore influencing the amount of hydrogen-related impurities in the chalcogenide glass.

Fig. 5: Ellingham diagrams of different oxygen compounds [25, 26].

For all of these reasons, it appears clearly that the choice of the getters, as well as the amount of getters used for the reactions, used has to be the result of a compromise between the reduction of the bands related to hydrogen and oxygen pollutions and the necessity to avoid as much as possible reactions involving the crucible[29–31].

As visible from Fig. 3.a, the process of casting has a small influence on both the background and the impurities, with just a small increasing of the Se – H band and the appearance of small peaks related to water and oxygen pollution. In addition, it has been shown that an optimized purification of the chalcogenide glass allows to mold and draw chalcogenide holey fibers with optical losses < 0.2 dB/m (at 5.5 μm) and Se – H absorption losses lower than 2 dB/m. This is the best transmission ever obtained in a selenide holey fiber.

5. Conclusions

The presented results show that it is possible to obtain high purity $\text{Ge}_{10}\text{As}_{22}\text{Se}_{68}$ by double distillation method, and that the efficacy of this method is heavily dependent on the choice of the getters. Between the ones tested, TeCl_4 and Mg seem to be the best candidates to minimize the incidence of both oxygen and hydrogen pollution on the optical losses of fibers.

Reactions between the getters and the silica crucibles used for this type of synthesis also appear to be possible, and need to be taken into consideration when choosing the species and amounts of halides and metals to introduce in the system.

The viability of casting method for obtaining high quality endlessly single mode fibers, with an attenuation lower than 0.2 dB/m at 5.5 μm , using this composition and a proper purification route is also demonstrated. This is of particular interest, seeing how chalcogenide microstructured optical fibers are an enabling technology for breakthroughs in the field of mid-infrared supercontinuum generation [13].

Acknowledgment

This project has received funding from the European Union's Horizon 2020 research and innovation program under Grant Agreement No. 722380.

References

- [1] J. Troles, V. Shiryayev, M. Churbanov, P. Houizot, L. Brillard, F. Désévéday, F. Charpentier, T. Pain, G. Snopatin, J.-L. Adam, Gese4 glass fibres with low optical losses in the mid-ir, *Optical Materials* 32 (1) (2009) 212–215.
- [2] J. Sanghera, I. Aggarwal, Active and passive chalcogenide glass optical fibers for ir applications: a review, *Journal of Non-Crystalline Solids* 256 (1999) 6–16.
- [3] J. Keirsse, C. Boussard-Plédel, O. Loreal, O. Sire, B. Bureau, B. Turlin, P. Leroyer, J. Lucas, Chalcogenide glass fibers used as biosensors, *Journal of non-crystalline solids* 326 (2003) 430–433.

- [4] J. M. Harbold, F. O. Ilday, F. W. Wise, B. G. Aitken, Highly nonlinear ge-as-se and ge-as-s-se glasses for all-optical switching, *IEEE Photonics Technology Letters* 14 (6) (2002) 822–824.
- [5] J. S. Sanghera, L. B. Shaw, P. Pureza, V. Q. Nguyen, D. Gibson, L. Busse, I. D. Aggarwal, C. M. Florea, F. H. Kung, Nonlinear properties of chalcogenide glass fibers, *International Journal of Applied Glass Science* 1 (3) (2010) 296–308.
- [6] M. Asobe, Nonlinear optical properties of chalcogenide glass fibers and their application to all-optical switching, *Optical Fiber Technology* 3 (2) (1997) 142–148.
- [7] Q. Coulombier, L. Brilland, P. Houizot, T. Chartier, T. N. N'guyen, F. Smektala, G. Renversez, A. Monteville, D. Méchin, T. Pain, et al., Casting method for producing low-loss chalcogenide microstructured optical fibers, *Optics Express* 18 (9) (2010) 9107–9112.
- [8] R. E. Slusher, G. Lenz, J. Hodelin, J. Sanghera, L. B. Shaw, I. D. Aggarwal, Large raman gain and nonlinear phase shifts in high-purity as₂se₃ chalcogenide fibers, *JOSA B* 21 (6) (2004) 1146–1155.
- [9] L. Fu, M. Rochette, V. Ta'eed, D. Moss, B. Eggleton, Investigation of self-phase modulation based optical regeneration in single mode as₂se₃ chalcogenide glass fiber, *Optics Express* 13 (19) (2005) 7637–7644.
- [10] M. Asobe, T. Kanamori, K. Kubodera, Ultrafast all-optical switching using highly nonlinear chalcogenide glass fiber, *IEEE photonics technology letters* 4 (4) (1992) 362–365.
- [11] U. Möller, Y. Yu, I. Kubat, C. R. Petersen, X. Gai, L. Brilland, D. Méchin, C. Caillaud, J. Troles, B. Luther-Davies, et al., Multi-milliwatt mid-infrared supercontinuum generation in a suspended core chalcogenide fiber, *Optics express* 23 (3) (2015) 3282–3291.
- [12] C. R. Petersen, U. Möller, I. Kubat, B. Zhou, S. Dupont, J. Ramsay, T. Benson, S. Sujecki, N. Abdel-Moneim, Z. Tang, et al., Mid-infrared supercontinuum covering the 1.4–13.3 μm molecular fingerprint region using ultra-high na chalcogenide step-index fibre, *Nature Photonics* 8 (11) (2014) 830.
- [13] C. R. Petersen, R. D. Engelsholm, C. Markos, L. Brilland, C. Caillaud, J. Trolès, O. Bang, Increased mid-infrared supercontinuum bandwidth and average power by tapering large-mode-area chalcogenide photonic crystal fibers, *Optics express* 25 (13) (2017) 15336–15348.
- [14] J. Knight, T. Birks, P. S. J. Russell, D. Atkin, All-silica single-mode optical fiber with photonic crystal cladding, *Optics letters* 21 (19) (1996) 1547–1549.
- [15] G. Renversez, B. Kuhlmeier, R. McPhedran, Dispersion management with microstructured optical fibers: ultraflattened chromatic dispersion with low losses, *Optics Letters* 28 (12) (2003) 989–991.
- [16] P. Toupin, L. Brilland, J. Trolès, J.-L. Adam, Small core ge-as-se microstructured optical fiber with single-mode propagation and low optical losses, *Optical Materials Express* 2 (10) (2012) 1359–1366.
- [17] J. Ballato, H. Ebendorff-Heidepriem, J. Zhao, L. Petit, J. Troles, Glass and process development for the next generation of optical fibers: A review, *Fibers* 5 (1) (2017) 11.
- [18] M. Churbanov, High-purity chalcogenide glasses as materials for fiber optics, *Journal of non-crystalline solids* 184 (1995) 25–29.
- [19] V. Shiryayev, M. Churbanov, E. Dianov, V. Plotnichenko, J. Adam, J. Lucas, Recent progress in preparation of chalcogenide as-se-te glasses with low impurity content, *Journal of optoelectronics and advanced materials* 7 (4) (2005) 1773.
- [20] D. Lezal, J. Pedlikova, J. Gurovic, R. Vogt, The preparation of chalcogenide glasses in chlorine reactive atmosphere, *Ceramics* 40 (2) (1996) 55–59.
- [21] 张斌, 杨志勇, 任和, 张鸣杰, 章健, 唐定远, Preparation method of high-purity and low-loss chalcogenide glass, *cN103332851B* (17 2015). URL <http://www.google.it/patents/US4741207>
- [22] V. Q. Nguyen, J. S. Sanghera, B. Cole, P. Pureza, F. H. Kung, I. D. Aggarwal, Fabrication of arsenic sulfide optical fiber with low hydrogen impurities, *Journal of the American Ceramic Society* 85 (8) (2002) 2056–2058.
- [23] S. Danto, D. Thompson, P. Wachtel, J. D. Musgraves, K. Richardson, B. Giroire, A comparative study of purification routes for as₂se₃ chalcogenide glass, *International Journal of Applied Glass Science* 4 (1) (2013) 31–41.
- [24] Z. Tang, V. S. Shiryayev, D. Furniss, L. Sojka, S. Sujecki, T. M. Benson, A. B. Seddon, M. F. Churbanov, Low loss ge-as-se chalcogenide glass fiber, fabricated using extruded preform, for mid-infrared photonics, *Optical Materials Express* 5 (8) (2015) 1722–1737.
- [25] T. B. Reed, Free energy of formation of binary compounds, MIT press, 1971.
- [26] W. Malcolm Jr, NIST-JANAF thermochemical tables, American Institute of Physics; The American Chemical Society, 1998.
- [27] W. M. Haynes, CRC handbook of chemistry and physics, CRC press, 2014.
- [28] V. Q. Nguyen, G. Drake, G. Villalobos, D. Gibson, S. Bayya, W. Kim, C. Baker, G. Chin, F. H. Kung, M. I. Kotov, et al., Effect of aluminum and tellurium tetrachloride addition on the loss of arsenic selenide optical fiber, *Optical Materials* 64 (2017) 327–333.
- [29] V. Shiryayev, S. Mishinov, M. Churbanov, Investigation of adhesion of chalcogenide glasses to silica glass, *Journal of Non-Crystalline Solids* 408 (2015) 71–75.
- [30] S. Mishinov, M. Churbanov, A. Gorokhov, D. Kazakov, V. Shiryayev, A. Suchkov, L. Igumnov, G. Snopatin, Adhesion mechanism of destruction of silica-glass surface during the preparation and treatment of optical glassy arsenic chalcogenides, *Inorganic Materials* 52 (7) (2016) 716–720.
- [31] M. Churbanov, S. Mishinov, V. Shiryayev, L. Ketkova, Contamination of glassy arsenic sulfide by sio₂ particles during melt solidification in silica glassware, *Journal of Non-Crystalline Solids* 480 (2018) 3–7.